

ELASTOBASE

TECHNICAL DATA SHEET
030610CAN15E
(supersedes 020108CAN1E)

DESCRIPTION

ELASTOBASE membranes are composed of a non-woven polyester reinforcement coated with oxidised bitumen. Both sides are sanded for bonding with hot bitumen.

FOR COMPLETE INFORMATION ON APPLICATION AND SYSTEMS, PLEASE CONSULT OUR SPECIFICATION MANUAL.

PROPERTIES

Properties	Standards	ELASTOBASE
Thickness	-	1.2 mm
Dimension	-	30 x 1 m
Underface	-	Sanded
Top face	-	Sanded
Reinforcement	-	Non-woven polyester
Storage	-	Upright on pallet
Breaking strength, MD/XD	CAN/CGSB-37.56-M 9 th draft	17 / 12.5 kN/m
Ultimate elongation, MD/XD	CAN/CGSB-37.56-M 9 th draft	60 / 65 %
Cold bending* - initial - 90 days at 70 °C	CAN/CGSB-37.56-M 9 th draft	≤ -5 °C
Softening point	ASTM D36	≥ 85 °C

(All values are nominal)