

## ELASTOCOL 350

TECHNICAL DATA SHEET  
131007SCAN4E  
(supersedes 130109SCAN2E)

### DESCRIPTION

**ELASTOCOL 350** is a stabilised bituminous emulsion (water based). It is used as a primer for waterproofing membranes, to enhance adhesion of torch-applied and self-adhesive membranes (**SOPRASOLIN**, **COLPHENE**, **SOPRASEAL STICK**, etc.) on most surfaces. It should be used in areas where solvent-based primers are not recommended.

### APPLICATION

**ELASTOCOL 350** can be applied by brush, roller or spray gun (the Airless process is not suitable) on wood decks, concrete, metal, bituminous systems, asphalt, etc.

Allow to dry completely before application of the membrane. Self-adhesive membranes should be applied the same day as the application of **ELASTOCOL 350**.

**Minimum Application Temperature: 5 °C (41 °F).**

**FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.**

### PROPERTIES

Properties	Standards	ELASTOCOL 350
Specific Gravity at 20 °C (68 °F)	-	1.00 kg/L
Solids by Weight	-	44 %
Colour	-	Dark Brown
Viscosity, Ford cup n°4, 20 °C (68 °F)	-	64 s
Drying time	-	Between 1 to 12 hours, depending on temperature and quantity applied.

(All values are nominal)

### PACKAGING

19 L pails

Average coverage: 0.15 to 0.25 L/m<sup>2</sup>.

### STORAGE & HANDLING

**Shelf life:** Up to 24 months in original sealed containers.

Storage temperature: 5 to 40 °C (41 to 104 °F). Do not freeze.

Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

ELASTOCOL 350 is not ruled by hazardous materials transport regulations.

**CONSULT THE MATERIAL SAFETY DATA SHEET PRIOR TO USE.**

