

# SOPRASEAL LM 200 T

TECHNICAL DATA SHEET 160530SCANE

(supersedes 110804SCAN2E)



WATERPROOFING

APPLICATIONS

WALLS

## DESCRIPTION

**SOPRASEAL LM 200 T** is a water-based single component, rubberised liquid product. **SOPRASEAL LM 200 T** is used as insulation adhesive or as an air/vapour barrier membrane. They are designed for use on most building materials, including masonry, concrete, wood and gypsum board in conjunction with rigid or semi-rigid thermal insulation boards (including polystyrene).

**SOPRASEAL LM 200 T** resists moisture and inhibits air leakage and moisture vapour transmission. It provides a highly flexible film bridging cracks, which may form in the substrate. It remains firmly bonded to the substrate even when applied over damp surfaces. It is not designed to be permanently exposed.

## APPLICATION

The substrate should be clean, sound, free of excess water and loose materials, grease and any contaminants, which may compromise the performance of the product. Apply **SOPRASEAL LM 200 T** with trowel and brush.

Minimum application and curing temperature: Install and allow material to dry at air and surface temperatures of 2 °C (35.6 °F) or higher. Curing times will be affected by relative humidity, temperature and airflow. The following times are given for average conditions and standard thickness. Actual times may differ depending on specific present on job at time of application.

Tack free film at 25 °C (77 °F) after 1 to 3 hours. 90% cure after 7 to 14 days. Complete cure after 30 days.

Application rate: Approximately 2 L/m<sup>2</sup>. A 19-litre pail will cover about 10 m<sup>2</sup> (100 ft<sup>2</sup>).

Film thickness: 2.3 mm (90 mil) wet, 1.15 mm (45 mil) dry.

**FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.**

## PACKAGING

Specifications	SOPRASEAL LM 200 T
Specific gravity at 20 °C (68 °F)	1.00 kg/L
Colour (Color)	Grey
Solids by Weight	52 %
Packaging	19 L (5 gal.)

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : SOPREMA INC. may modify the composition and/or use of its products without prior notice.

TDS\_SOPRASEAL\_LM\_200 T.indd

# SOPRASEAL LM 200 T

TECHNICAL DATA SHEET 160530SCANE

(supersedes 110804SCAN2E)



WATERPROOFING

APPLICATIONS

WALLS

## PROPERTIES

Properties	Standards	SOPRASEAL LM 200 T
Water vapour permeance	ASTM E96	34.2 ng/Pa•s•m <sup>2</sup> (0.6 perm)
Air permeability	ASTM E283 (75 Pa)	< 0.0007 L/s•m <sup>2</sup>
Resistance to gust wind load	ASTM E330 (3000 Pa – 10 s)	Complies
Resistance to sustained wind load	ASTM E330 (100 Pa – 1 h)	Complies

(All values are nominal)

## CLEANING

Uncured material can be cleaned using light soap and water. Cured material is best removed by solvents such as mineral spirits, Varsol, Xylene or by mechanical means.

## STORAGE AND HANDLING

**Shelf life:** Up to 2 years in original sealed containers. **KEEP FROM FREEZING!**

SOPRASEAL LM 200 T is not ruled by hazardous materials transport regulations. Keep out of reach of children. Harmful if inhaled, swallowed or when in contact with the skin. Do not pour residues in drains.

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : SOPREMA INC. may modify the composition and/or use of its products without prior notice.

TDS\_SOPRASEAL\_LM\_200 T.indd