

SOPRAMASTIC LM

**SOPREMA**

SOPREMA MIDDLE EAST
P.O. Box 37 1013, Dubai Airport Free Zone
Building E5A - Office 512
Phone: + 97 1 4 609 1661
info@soprema.ae

TECHNICAL DATA SHEET
140422SME1E
(supersedes 140326SME1E)

DESCRIPTION

SOPRAMASTIC LM is a black bituminous mastic containing asphalt, solvents, mineral stabilizers and fibers.

APPLICATIONS

SOPRAMASTIC LM is a multi purpose paste type of mastic that can be applied by trowel or spatula for various applications, to fill cracks and seal joints.

PREPARATION

Must be applied on sound substrate.

The surfaces should be dry, clean and free from loose material.

INSTALLATION

Excellent adhesion on most materials without primer.

It can be applied on damp surfaces.

HEALTH & ENVIRONMENT

The membrane does not contain any substance that might be detrimental to health or to the environment and complies with generally accepted health standards and Material Safety Data Sheet (MSDS).

QUALITY CONTROL

SOPREMA has always attached the highest importance to quality control. For this reason, we operate an internationally recognized quality system meeting ISO 9001 & ISO 14001 standards, independently monitored and certified.

PACKAGING

Specifications	SOPRAMASTIC LM
Type of solvent	Aliphatic with some aromatic hydrocarbon solvent.
Containers	Supplied in 15L and 20L pails.
Storage	Shelf life from 12-18 months under good storage conditions.

Compatible with bituminous materials.

Used as jointing mastic and joint filler.

Ensures good waterproofing.

Soft and flexible coating.



SYSTÈME QUALITÉ
ISO 9001
QUALITY SYSTEM



SYSTÈME ENVIRONNEMENT
ISO 14001
ENVIRONMENT SYSTEM

SOPRAMASTIC LM

**SOPREMA**

SOPREMA MIDDLE EAST
P.O. Box 37 1013, Dubai Airport Free Zone
Building E5A - Office 512
Phone: + 97 1 4 609 1661
info@soprema.ae

TECHNICAL DATA SHEET
140422SME1E
(supersedes 140326SME1E)

PROPERTIES

SOPRAMASTIC LM complies with the requirements of ASTM D4586, Type II.

Properties	SOPRAMASTIC LM
Flash point	50 °C approx.
Specific gravity	1.05 approx.
Coverage	3 L/m ² (3 mm wet thickness).
Drying time	Most of the solvent will evaporate during 24 hours. The mastic layer remains sort for many months.
Chemicals and water resistance	Resistant to water, salt solutions, dilute acids and alkalis.
Heat flow resistance	The cured film does not sag or flow under normal conditions.
Flexibility	Provides a soft flexible coating.

(All values are nominal)

CLEANING

Clean the tools with Kerosene or white spirit.



SYSTÈME QUALITÉ
ISO 9001
QUALITY SYSTEM



SYSTÈME ENVIRONNEMENT
ISO 14001
ENVIRONMENT SYSTEM