





APPLICATIONS

ROOFING BALCONIES

FLASHING REINFORCEMENT

TECHNICAL DATA SHEET APTDS-E-76-01

DESCRIPTION

FLASHING REINFORCEMENT is 100 % polyester stitch-bonded fabric. This high performance reinforcement is made without the use of a chemical binder.

FLASHING REINFORCEMENT is used in conjunction with **ALSAN FLASHING**. Its high absorption capability allows to quickly wet into and become encapsulated by **ALSAN FLASHING** liquid membrane.

PROPERTIES

Properties	Standards	FLASHING REINFORCEMENT
Roll Size	-	0.15 x 30.5 m (6 in x 100 ft)
Average Thickness	-	0.6 mm (25 mil)
Average Net Weight	-	100 g/m² (3 ounce per square yard)
Tensile Strength	ASTM D1682	393 kPa (57 psi)
Elongation	ASTM D1682	62 %
Tear Strength	ASTM D1117	71 N (16 lbf)
Mullen Burst	ASTM D3786	783 N (176 lbf)

(All values are nominal)





