

SOPRA-SPF 500

TECHNICAL DATA SHEET 190531SCANE

(supersedes 190402SCANF)



INSULATION
SOUNDPROOFING

APPLICATIONS

WALLS

INDOOR APPLICATIONS

DESCRIPTION

SOPRA-SPF 500 is a two-component, open-cell, spray-applied polyurethane foam insulation system. SOPRA-SPF 500 is designed for interior commercial, industrial and residential insulation and soundproofing applications. It is 100% water-blown i.e. no hydrofluorocarbons (HFC).

SOPRA-SPF 500 is used for hard to reach areas and has excellent acoustical dampening properties.

RECOMMENDED SUBSTRATES

This product can be used on most substrates such as masonry, concrete, wood, metal and gypsum.

SURFACE PREPARATION

The substrate to be sprayed on should be free of dirt, soil, grease, oil and moisture prior to the application of either SOPRA-SPF 500. Moisture in any form such as excessive relative humidity (> 85% R.H.), rain, fog, or ice will react chemically and will adversely affect the system performance and corresponding physical properties.

APPLICATION

SOPRA-SPF 500 must be applied with a spray gun. Mix the SOPRA-SPF 500 RESIN 20 minutes before start-up. Then, mix the two components, SOPRA-SPF 500 RESIN and SOPRA-SPF ISO, with a 1:1 ratio by volume. Always maintain the SOPRA-SPF 500 RESIN mixing at low speed.

- Application temperatures:

SOPRA-SPF 500 : 5 °C to 50 °C (41 °F to 122 °F)

- Maximum service temperature:

SOPRA-SPF 500 : 82 °C (180 °F)

SOPRA-SPF 500 meets the requirements of the GREENGUARD certification.



EQUIPMENT

A mechanical purge spray gun is recommended for highest foam quality. It is dispensed through an approved transfer pump that can deliver a 2:1 ratio from the container to the proportioner to ensure the specified 1:1 ratio. Hose heaters should be set to deliver 54 °C to 59 °C (130 °F to 135 °F) material to the spray gun. Recommended spraying pressure: 1,000 to 1,500 psi (69 to 103 bar), depending on hose length.

RESTRICTIONS

SOPRA-SPF 500 may only be installed by a certified installer as per ISO 17024 SPF and CAN/ULC-S712.2 Standards

Extreme care must be taken when removing and reinstalling transfer pumps so as not to interchange the two components.

If the product is below storage temperatures, the increased viscosity of the components may cause pump cavitation resulting in inadequate SPF application. If the product is above storage temperatures, there may be a loss of blowing agent resulting in diminished yield. Keep from freezing.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

SOPRA-SPF 500



INSULATION
SOUNDPROOFING

APPLICATIONS

WALLS

INDOOR APPLICATIONS

TECHNICAL DATA SHEET 190531SCANE

(supersedes 190402SCANF)

PACKAGING

Specifications	SOPRA-SPF 500
Colour	Yellow
Hose temperature (A and B)	54 °C to 59 °C (130 °F to 135 °F)
Mix ratio parts	1 : 1
Specific gravity @ 25 °C (77 °F) Part A* Part B**	1.24 kg/L 1.1 kg/L
Viscosity, Brookfield at 25 °C (77 °F) Part A* Part B**	150-350 cP 400-700 cP

*Part A : SOPRA-SPF ISO

**Part B : SOPRA-SPF 500 RESIN

(All values are nominal)

WEIGHT

Dimensions	SOPRA-SPF 500
Drum Part A* Part B**	227 kg (500 lb) 227 kg (500 lb)

*Part A : SOPRA-SPF ISO

**Part B : SOPRA-SPF 500 RESIN

(All values are nominal)



SOPRA-SPF 500



INSULATION
SOUNDPROOFING

APPLICATIONS

WALLS

INDOOR APPLICATIONS

TECHNICAL DATA SHEET 190531SCANE

(supersedes 190402SCANF)

PROPERTIES

Properties	Standards	SOPRA-SPF 500
Density	ASTM D1622	6.8 kg/m ³ (0.45 lb/ft ³)
Initial thermal resistance, 25 mm	ASTM C518	0.62 RSI (R 3.5)
Aged thermal resistance, 25 mm 90 days at 60 °C (140 °F)	ASTM C518	0.62 RSI (R 3.5)
Tensile strength	ASTM D1623	23 kPa (3.3 lb/in ²)
Water absorption	ASTM D2842	17.4% by volume
Water vapour permeance, 50 mm (2 in)	ASTM E96 (method B)	1580 ng/Pa·s·m ² (28 perm)
Dimensional stability (after 28 days): - at -29 °C (-20 °F) - at 80 °C (176 °F) - at 70 °C (158 °F), 95% RH	ASTM D2126	- 0.1% change of volume 0% change of volume - 0.1% change of volume
Surface burning characteristics**, flame spread	CAN/ULC-S102 *ASTM E84	< 210
Surface burning characteristics, smoke index	CAN/ULC-S102 *ASTM E84	< 195
Surface burning characteristics**, flame spread	CAN/ULC-S127	< 315
Fungi resistance	ASTM C1338	No growth
VOC emissions***	CAN/ULC-S774 *CA 01350	Pass

For CCMC product evaluation see CCMC Evaluation listing 14108-R/ * ICC-ES ESR-4411.

(All values are nominal)

SOPRA-SPF 500 meets and exceeds CAN/ULC-S712.1 standard.

** These numerical flame spread values are not a true reflection on how this or any material will perform in actual fire conditions.

*** 24 hours cure time, no occupancy.



SOPRA-SPF 500

TECHNICAL DATA SHEET 190531SCANE

(supersedes 190402SCANF)



INSULATION
SOUNDPROOFING

APPLICATIONS

WALLS

INDOOR APPLICATIONS

STORAGE AND HANDLING

SOPRA-SPF 500 must be stored between 18 °C and 26 °C (64 °F to 79 °F) in a dry and well-ventilated area, before and during the application. If this is not possible, the conditioning of the product must be done 24 hours before the application for the drums.

Pressure inside the container may increase to the point of rupture if stored under direct sun or at temperatures over 60 °C (140 °F). These conditions may also affect the quality of the product. Do not configure the equipment to recirculate SOPRA-SPF 500 components from proportioner back into the containers. Do not recirculate or mix other supplier components into SOPRA-SPF 500 containers. Keep from freezing.

Shelf life of SOPRA-SPF ISO (Part A): 1 year

Shelf life of SOPRA-SPF 500 RESIN (Part B): 6 months

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).

