

COLPHENE 3000

TECHNICAL DATA SHEET ANZ-TDS-10-COLPHENE 3000

DESCRIPTION

COLPHENE 3000 is a self-adhesive waterproofing membrane composed of SBS modified bitumen and a tri-laminated woven polyethylene facer. The underface is covered with silicone release film.

COLPHENE 3000 is design for foundation walls and other below grade vertical surfaces.

RECOMMENDED SUBSTRATES

This product can be used on most building surfaces, such as masonry, concrete and wood.

SURFACE PREPARATION

The use of SOPRASEAL STICK PRIMER, ELASTOCOL STICK ZERO or ELASTOCOL STICK H2O primer is recommended before the installation of COLPHENE 3000 membrane. The substrate should be clean, sound, free of excess water and loose materials, grease and any contaminants, which may compromise the performance of the product.

INSTALLATION

SELF-ADHESIVE

COLPHENE 3000 membrane must be adhered to support by peeling off the silicone release film.

Side lap joints must be a minimum of 75 mm (3 in) and end lap joints must be a minimum of 150 mm (6 in).

Once installed, a pressure must be applied over the whole surface using a membrane roller to ensure good contact.

The uppermost edge of the membrane shall be mechanically fastened using termination bars and sealed with SOPRAMASTIC.

Application temperatures: Winter grade: -10 to 10°C (14 to 50°F)

Summer grade: 10 to 50°C (50 to 122°F)

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	COLPHENE 3000
Thickness	1.5 mm
Dimensions	1 × 18.7 m
Weight	1.5 kg/m ²
Selvedge width	75 mm
Surface	Tri-laminated woven polyethylene
Underface	Silicone release film
Qty/pal	30

COLPHENE 3000

TECHNICAL DATA SHEET ANZ-TDS-10-COLPHENE 3000

PROPERTIES

Properties	Standards	COLPHENE 3000
Tensile strength, MD/XD	ASTM D5147	11.3 / 15.4 kN/m
Tensile strength, MD/XD	ASTM D412	11.2 / 13.1 MPa
Ultimate elongation, MD/XD	ASTM D412	88 / 55%
Ultimate elongation, MD/XD	ASTM D5147	40 / 25%
Elongation of rubberised asphalt	ASTM D5147	> 1000 %
Flexibility at cold temperature	ASTM D5147	- 35°C
Static puncture	ASTM E154	747 N
Static puncture	ASTM D5602	400 N
Tear resistance, MD/XD	ASTM D5601	375 / 400 N
Lap adhesion	ASTM D1876	2000 N/m
Water absorption	ASTM D5147	0.1 % max
Peel resistance	ASTM D903	3500 N/m
Water vapour permeance	ASTM E96 (Procedure B)	0.49 ng/Pa·s·m ² (0.0086 perm)
Crack cycling at -32°C (25.6°F), 100 cycles	ASTM C836	Unaffected
Resistance to hydrostatic head	ASTM D5385	114 m min.
Adhesion strength to concrete - Not primed - Combined with primer	ASTM D1000	560 N/m 1650 N/m

For CCMC product evaluation see CCMC Evaluation listing #13560-R

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the product is stored outdoors, cover them with an opaque protective cover after removal of the delivery packaging.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative or the contractor is responsible for checking the suitability of products for their intended use.

Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by Soprema Australia Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Soprema Australia Pty Ltd are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	COLPHENE 3000
Initial Issue	03.07.2019
Amendment	
Author	SB