



INSULATION

APPLICATIONS

ROOFS

# SOPRA-ISO PLUS SHIPLAP BOARD

TECHNICAL DATA SHEET 200127SCANF

(supersedes 190304SCANF)

## DESCRIPTION

SOPRA-ISO PLUS SHIPLAP BOARD is a polyisocyanurate thermal insulation board with shiplap edges on four (4) sides. It is composed of a closed cell polyisocyanurate foam core between polymers coated glass fibres facers.

It is mainly used as thermal insulation for SOPREMA roofing systems.

## INSTALLATION

### MECHANICALLY FASTENED

Mechanically fastened with screws and stress plates for insulation.

### ADHERED WITH HOT BITUMEN

Adhered with hot bitumen (the temperature of the bitumen must be 10 °C (50 °F) below the Equiviscous Temperature (EVT<sup>1</sup>).

### ADHERED WITH ADHESIVE

Adhered with one of the DUOTACK adhesives.

The required number of mechanical fasteners and amount of adhesive varies from zone to zone. For more details about these requirements, consult the Wind Uplift Resistance Testing reports according to Canadian standard CSA A123.21 or Factory Mutual (FM 4470).

Service temperature: -73 to 122 °C (-100 to 250 °F)


## RESTRICTIONS

Waterproofing membranes must not be adhered directly to SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation board, except COLVENT BASE 830 (without primer) and COLVENT BASE 840 (with primer). SSOPRA-ISO PLUS SHIPLAP BOARD thermal insulation boards of 1200 x 2400 mm (4 ft x 8 ft) must not be adhered with hot bitumen or adhesive. Otherwise, a recovery board for roofing must be put in place before the installation of any other waterproofing membranes.

Installation methods	BOARD 1.2 x 1.2 m (47.4 x 47.4 in)	BOARD 1.2 x 2.4 m (47.4 x 96 in)
Mechanically fastened	Wook deck ONLY	YES
Adhered with hot bitumen	YES	NO
Adhered with adhesive	YES	NO

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	SOPRA-ISO PLUS SHIPLAP BOARD
Thickness	88.9 to 152.4 mm (3.5 to 6 in)*
Dimensions of the boards	1.2 x 1.2 m (47.4 x 47.4 in) & 1.2 x 2.4 m (47.4 x 96 in)
Shiplap dimensions	
Surface	Polymers coated glass fibres facers
Underface	Polymers coated glass fibres facers

\*Others thicknesses available upon request.  
(All values are nominal)

1.Equiviscous Temperature (EVT): The temperature at which bitumen reaches an ideal viscosity threshold of 125 cP (0.125 Pa.s), which guarantees the quantity of mop-applied inter-ply asphalt used in laminated roofing systems ([www.roofingcanada.com](http://www.roofingcanada.com)).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRA-ISO\_PLUS\_SHIPLAP\_BOARD.indd

1/2

# SOPRA-ISO PLUS SHIPLAP BOARD

TECHNICAL DATA SHEET 200127SCANF

(supersedes 190304SCANF)



INSULATION

APPLICATIONS

ROOFS

## PROPERTIES

SOPRA-ISO SHIPLAP BOARD thermal insulation meets the physical property requirements of ASTM C 1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC S704 Type II (20 psi) and Type III (25 psi).

Properties	Standards	SOPRA-ISO SHIPLAP BOARD
Thermal Resistance (LTTR) (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])		
88.9 mm (3 ½ in) 101.6 mm (4 in) 114.3 mm (4 ½ in) 127 mm (5 in) 152.4 mm (6 in)	CAN/ULC S704-11	3.60 RSI (R – 20.5) 4.15 RSI (R – 23.6) 4.72 RSI (R – 26.8) 5.25 RSI (R – 29.8) 6.29 RSI (R – 35.7)
Metal Deck Maximum Flute Spanability based on SOPRA-ISO thickness		
≥ 25.40 mm (1.0 in) < 35.56 mm (1.4 in) > 38.10 mm (1.5 in) ≤ 152.4 mm (6 in)	-	66.70 mm (2 5/8 in) 111.10 mm (4 3/8 in)
Compressive Strength	ASTM D 1621	138 kPa (20 psi) 172 kPa (25 psi)
Density	ASTM D 1622	32 kg/m <sup>3</sup> (2.0 lb/ft <sup>3</sup> )
Linear Dimensional Stability	ASTM D 2126	< 0.5 %
Water Absorption	ASTM C 209 ASTM D 2842	< 1.0 % < 3.5 %
Flame Spread*	ASTM E 84	40 - 60
Tensile Strength	ASTM D 1623	35 kPa (> 730 lb/ft <sup>2</sup> )

\*The numerical ratings as determined by ASTM Test Method E 84 are not intended to reflect hazards presented by this or any other material under actual fire conditions.  
(All values are nominal)

## STORAGE AND HANDLING

The SOPRA-ISO SHIPLAP BOARD thermal insulation boards are covered with a waterproof packaging for handling the panels in the manufacturing plant and during transit only.

SOPRA-ISO SHIPLAP BOARD thermal insulation boards must be stored on a flat substrate and sheltered from inclement weather. In addition, the temporary SOPREMA applied packaging must be removed to prevent accumulation of condensation.

When short-term outdoor storage is necessary, SOPRA-ISO SHIPLAP BOARD thermal insulation boards must be stacked on skids at least 75 mm (3 in) above the ground, store flat and cover with a waterproof cover such as a canvas tarpaulin.

Refer to PIMA Technical Bulletin No. 109: Storage & Handling Recommendations for Polyiso Roof Insulation at [www.polyiso.org](http://www.polyiso.org).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS\_SOPRA-ISO\_PLUS\_SHIPLAP\_BOARD.indd