

SOPRA-XPS 35



INSULATION

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 200115SCANE

(supersedes 190903SCANE)

DESCRIPTION

SOPRA-XPS 35 is a rigid thermal insulation board made of extruded polystyrene composed of closed cell foam.

SOPRA-XPS 35 is available with shiplap edges on all four sides in several thickness and square edges in the thickness of 25 mm (1 in).

It is mainly used as a thermal insulation for **SOPREMA** protected-membrane roofing systems (inverted roofs).

SOPRA-XPS 35 does not have any CFC and HCFC - Zero ozone depletion potential.

Over 25% post-consumer and post industrial recycled content.

SOPRA-XPS 35 has low VOC emissions, it has been tested and determined compliant in accordance with *California Department of Public Health (CDPH) V1.2 (January 2017)*.

SOPRA-XPS 35 meets GREENGUARD GOLD certification.

INSTALLATION

LOOSE LAID

Boards are laid flat on the roof. When another layer of **SOPRA-XPS 35** insulation is required, it should be installed with staggered joints without being adhered to the first layer. If necessary, use an adhesive compatible with extruded polystyrene to hold the panels together temporarily.

Maximum service temperature: 75 °C (167 °F).


LIMITATIONS

The printed side of **SOPRA-XPS 35** insulating boards must be installed directly on the substrate.

SOPRA-XPS 35 should not be exposed to UV rays for more than 60 days.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	SOPRA-XPS 35
Available thicknesses* for shiplap boards	38 mm (1.5 in) 51 mm (2 in) 64 mm (2.5 in) 76 mm (3 in) 89 mm (3.5 in) 102 mm (4 in)
Available thicknesses* for square boards	25 mm (1 in)
Dimensions of the boards*	2438 mm X 610 mm (8 x 2 ft)
Shiplap dimensions	
Colour	Light orange

*Other thicknesses and dimensions available upon request.
(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

SOPRA-XPS 35



INSULATION

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 200115SCANE

(supersedes 190903SCANE)

PROPERTIES

SOPRA-XPS 35 meets the requirements of CAN/ULC S701.1 Type 4 (ASTM C578-14 Type IV).

Properties	Standards	SOPRA-XPS 35
Thermal Resistance ¹ (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])	ASTM C518	RSI- 0.88 (R – 5.0)
Water Vapour Permeance	ASTM E96	52 ng/Pa·m ² ·s (0.9 perm)
Flame spread rating	CAN/ULC-S102.2 ²	> 25 < 500
Dimensional Stability	ASTM D2126	Pass
Min. Flexural Strength	ASTM C203	640 kPa (93 psi)
Water Absorption, % by volume, max.	ASTM D2842	0.7
Min. Compressive Strength ³	ASTM D1621	241 kPa (35 psi)
Limiting Oxygen Index	ASTM D2863	24 %

For CCMC product evaluation see CCMC Evaluation listing 14149-L

(All values are nominal)

¹ The long-term thermal performance (LTTR) of SOPRA-XPS 35 complies with CAN/ULC S701.1 standard requirement: min. RSI-1.66 (R-9.4) for Type 4 products that are 50 mm (2 in) thick. Please consult your SOPREMA representative for more information.

² CAN/ULC-S102.2 : Standard Method of Test for Surface Burning Characteristics of Flooring Covering and Miscellaneous Materials and Assemblies.

³ At 5% deformation or yield.

STORAGE AND HANDLING

SOPRA-XPS 35 thermal insulation boards are covered with a temporary waterproof packaging for handling the panels in the manufacturing plant and during transit.

SOPRA-XPS 35 thermal insulation boards must be stored on a flat substrate in their original packaging. If the products are stored outdoors, cover them with an opaque protective cover if the original packaging is removed so that the boards are always protected from UV and sheltered from inclement weather. As they are flammable, they must be protected and kept away from flames and intense heat sources during transportation, handling, storage, and installation.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.