

SOPRASEAL

LM 202 VP

TECHNICAL DATA SHEET 190924SCANE

(supersedes 180823SCANE)



WATERPROOFING

APPLICATIONS

WALLS

DESCRIPTION

SOPRASEAL LM 202 VP is a single component liquid, made from modified rubber. SOPRASEAL LM 202 VP is used as an vapour permeable air barrier and provides moisture protection behind wall claddings including brick, siding, metal panels, EIFS and stucco. Utilization of a slipsheet is required for stucco cladding.

RECOMMENDED SUBSTRATES

This product can be used on most building surfaces, such as masonry, concrete, wood and gypsum.

SOPRASEAL LM 202 VP can also be used with SOPRASEAL STICK FLASHPRO HT and SOPRASEAL STICK 1100 T membranes at openings.

SURFACE PREPARATION

The substrate should be clean, sound, dry and free of loose materials, grease and any contaminants, which may compromise the performance of the product.

APPLICATION

Apply SOPRASEAL LM 202 VP at openings, sheathing joints, inside and outside corners and immediately place SOPRASEAL QUICK CORNER at corner openings and SOPRASEAL MESH at openings, sheathing joints, inside and outside corners. SOPRASEAL QUICK CORNER and SOPRASEAL MESH must be completely saturated with SOPRASEAL LM 202 VP.

To apply SOPRASEAL LM 202 VP use a 19 mm (¾ in) nap roller, paint brush or spray equipment.

Use SOPRASEAL SEALANT with SOPRASEAL LM 202 VP membrane to seal around details and critical areas.

Minimum application temperature: 4 °C (40 °F). To apply SOPRASEAL LM 202 VP at temperatures below 4 °C (40 °F), but above -4 °C (25 °F), blend 1 entire quart container of SOPRASEAL LT ADDITIVE.

Allow to dry completely, typically 2 to 4 hours at 25°C (77°F) and 50% relative humidity.

THICKNESS ACCORDING TO SUBSTRATE

Substrats	Number of coat	Wet film thickness
Exterior sheathing, cement-boards (ASTM C1325 Type A Exterior), gypsum sheathing (ASTM C79/ASTM C1396).	1 coat	0.25 mm (10 mil)*
Concrete/masonry treated with SOPRASEAL LM BLOCK FILLER (fully cured).	1 coat	0.50 mm (20 mil)*
Concrete/masonry not treated with SOPRASEAL LM BLOCK FILLER, plywood and OSB.	2 coats	0.25 mm (10 mil)*

*Use a wet film gauge to confirm the wet film thickness of SOPRASEAL LM 202 VP.
(All values are nominal)

EQUIPMENT

The use of a 25/30 ¼" MEG tip with spraying equipment comprising a diaphragm pump and a minimum of 5 HP compressor (minimum 30 gallons) is recommended.

Recommended spraying pressure: 45 psi.

UV exposure: up to 180 days

RESTRICTION

Do not use SOPRASEAL LM 202 VP for below grade applications or on surfaces subject to water immersion.

For proper curing, the minimum curing temperature is 4 °C (40 °F) and it must be maintained for the length of curing process.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

SOPRASEAL LM 202 VP

TECHNICAL DATA SHEET 190924SCANE

(supersedes 180823SCANE)



WATERPROOFING

APPLICATIONS

WALLS

PACKAGING

Specifications	SOPRASEAL LM 202 VP
Colour	Red-brown
Solids	74%
Coverage per 19 L pail, depending on substrate*	
Gypsum	41 m ² (450 ft ²)
Plywood / OSB	24 m ² (265 ft ²)
Concrete masonry unit (CMU)	14 m ² à 24 m ² (150 ft ² à 265 ft ²)
Poured concrete	46 m ² (500 ft ²)
Concrete / masonry with SOPRASEAL LM BLOCK FILLER	46 m ² (500 ft ²)
Embedded SOPRASEAL MESH per pail**	100 mm (4") / 192 m (630 ft) 150 mm (6") / 128 m (420 ft) 230 mm (9") / 85 m (280 ft)
Dimensions of Sopraseal Mesh	4" Sheathing fabric: 101.5 mm x 54.8 m (4" x 180 ft) roll 6" Sheathing fabric: 152.4 mm x 54.8 m (6" x 180 ft) roll 9" Sheathing fabric: 228.5 mm x 54.8 m (9" x 180 ft) roll

* Coverage rates are approximative and may vary due to the application technique and substrates.

** SOPRASEAL MESH saturated with SOPRASEAL LM 202 VP, when applied per manufacturer instructions, self gauges to 0,75-1 mm (30-40 mil) thickness.
(All values are nominal)

PROPERTIES

Properties	Standards	SOPRASEAL LM 202 VP
Air leakage resistance (assembly) - 75 Pa (1.57 psf) positive / post conditioning - 75 Pa (1.57 psf) negative / post conditioning	ASTM E2357	0.0007 L/s•m ² (0.0001 cfm/ft ²) 0.0014 L/s•m ² (0.0003 cfm/ft ²)
Air permeability - 75 Pa (1.57 psf)	ASTM E2178	0.0049 L/s•m ² (0.00098 cfm/ft ²)
Rate of air leakage	ASTM E283	0.0185 L/s•m ² (0.0037 cfm/ft ²)
Water vapour transmission - 0.5 mm (20 mil) wet film thickness - 0.25 mm (10 mil) wet film thickness	ASTM E96 Method B	800 ng/Pa•s•m ² (14 perm) 1030 ng/Pa•s•m ² (18 perm)
Pull-off strength of coatings	ASTM D4541	Pass - Min, 110 kPa (15.9 psi) or substrate failure (tested over gypsum sheathing)
Nail sealability (without sheathing fabric)	ASTM D1970	Pass
Compound stability (elevated temperature)	ASTM D5147 (section 15)	No flowing, dripping or drop formation up to 177 °C (350 °F)

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS_SOPRASEAL_LM_202_VP.indd

SOPRASEAL LM 202 VP



WATERPROOFING

APPLICATIONS

WALLS

TECHNICAL DATA SHEET 190924SCANE

(supersedes 180823SCANE)

PROPERTIES

Properties	Standards	SOPRASEAL LM 202 VP
Surface burning - Class A flame spread - Class A smoke developed spread	ASTM E84	< 25 < 450
Fire resistance	ASTM E119/UL263 NFPA 285	Will not add or detract the rating of a fire resistive wall assembly Pass
Resistance to fungal defacement	ASTM D5590	Pass

ICC-ES AC 212 ACCEPTANCE CRITERIA FOR WATER-RESISTIVE COATINGS USED AS WATER-RESISTIVE BARRIERS OVER EXTERIOR SHEATHING

SEQUENTIAL TESTING: PROPERTIES

Properties	Standards	SOPRASEAL LM 202 VP
1- Structural 2- Racking 3- Restrained environmental conditioning 4- Water penetration @ 299 Pa (6.24 psf)	ASTM E1233 Procedure A ASTM E72 ICC-ES AC 212 ASTM E331	(1-3) No cracking at joints or interface of flashing (4) No water penetration after 90 min, tested over OSB and gypsum sheathing

SEQUENTIAL TESTING - WEATHERING: PROPERTIES

Properties	Standards	SOPRASEAL LM 202 VP
1- UV light exposure 2- Accelerated aging 3- Hydrostatic pressure test	ICC-ES AC 212 ICC-ES AC 212 AATC 127-1985	(1-2) No cracking or bond failure to substrate (3) No water penetration
Water resistance	ASTM D2247	No sign of deleterious effects after 14 day exposure (tested over various substrates)
Freeze-thaw	ASTM D2485 Method B	No sign of deleterious effects after 10 cycles (tested over various substrates)
Tensile bond (before and after freeze-thaw), kPa (psi)	ASTM C297	> 103 (15) avg; no failure after 10 cycles freeze-thaw (tested over various substrates)
Tensile bond, kPa (psi)	ASTM C297	> 103 (15) (tested over various substrates)

(All values are nominal)

STORAGE AND HANDLING

Shelf life: Approximately 24 months, properly stored in original unopened containers. Protect from freezing, extreme heat and direct sunlight.

FOR MORE INFORMATION, REFER TO INSTRUCTIONS ON THE CONTAINER LABEL AND RELEVANT SAFETY DATA SHEET (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS_SOPRASEAL_LM_202_VP.indd