

## **APPLICATIONS**

**ROOFS** 

# SOPRA-ISO PLUS TAPERED

TECHNICAL DATA SHEET 200921SCANF

supersedes 200127SCANF

## **DESCRIPTION**

**SOPRA-ISO PLUS TAPERED** is a sloped polyisocyanurate thermal insulation board. It is composed of a closed cell polyisocyanurate foam core between polymers coated glass fibres facers.

**SOPRA-ISO PLUS TAPERED** is designed to promote positive drainage to prevent ponding water and used as thermal insulation for **SOPREMA** roofing systems.

## **INSTALLATION**

#### MECHANICALLY FASTENED\*

Mechanically fastened with screws and stress plates for insulation.

#### ADHERED WITH HOT BITUMEN

Adhered with hot bitumen (the temperature of the bitumen must be 10 °C (50 °F) below the Equiviscous Temperature (EVT1).

#### ADHERED WITH ADHESIVE\*

Adhered with one of the DUOTACK adhesives.

Service temperature: -73 to 122 °C (-100 to 250 °F)

\*The required number of mechanical fasteners and amount of adhesive varies from zone to zone. For more details about these requirements, consult the Wind Uplift Resistance Testing reports according to Canadian standard CSA A123.21 or Factory Mutual (FM 4470)

#### RESTRICTIONS

Waterproofing membranes must not be adhered directly to SOPRA-ISO PLUS TAPERED thermal insulation board, except COLVENT BASE 830 (without primer) and COLVENT BASE 840 (with primer). Otherwise, a recovery board for roofing must be put in place before the installation of any other waterproofing membranes.

SOPRA-ISO PLUS TAPERED thermal insulation board of 1200 x 2400 mm (4 ft x 8 ft) must not be adhered with hot bitumen or adhesive.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## **PACKAGING**

Specifications	SOPRA-ISO PLUS TAPERED		
Thickness	13 mm to 100 mm (0.5 to 4 in)*		
Dimensions	1.22 x 1.22 m (4 x 4 ft) 1.22 x 2.44 m (4 x 8 ft)*		
Surface	Polymers coated with glass fibres facers		
Underface	Polymers coated with glass fibres facers		
Available slopes	$\begin{array}{ccccc} 0.5 \% \ (^{1}\!/_{16} \ in/ft) & 1 \% \ (^{1}\!/_{8} \ in/ft) & 1.5 \ \% \ (^{3}\!/_{16} \ in/ft) \\ 2 \% \ (^{1}\!/_{16} \ in/ft) & 3 \% \ (^{3}\!/_{8} \ in/ft) & 4 \% \ (^{1}\!/_{2} \ in/ft) \end{array}$		

<sup>\*</sup>Others thicknesses available upon request.

<sup>1.</sup>Equiviscous Temperature (EVT): The temperature at which bitumen reaches an ideal viscosity threshold of 125 cP (0.125 Pa.s), which guarantees the quantity of mop-applied inter-ply asphalt used in laminated roofing systems (www. roofingcanada.com)



SYSTÈME QUALITÉ ISO 9001 QUALITY SYSTEM



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

<sup>(</sup>All values are nominal)



# SOPRA-ISO PLUS TAPERED

APPLICATIONS

**ROOFS** 

TECHNICAL DATA SHEET 200921SCANF

supersedes 200127SCANF)

## **PROPERTIES**

**SOPRA-ISO PLUS TAPERED** thermal insulation board meets the physical property requirements of ASTM C 1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC S704 Type II (20 psi) and Type III (25 psi).

Properties	Standards	SOPRA-ISO PLUS TAPERED
Thermal Resistance (LTTR) (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])  25.40 mm (1.0 in) 38.10 mm (1.5 in) 50.80 mm (2.0 in)	CAN/ULC S704-11	1.00 RSI (R – 5.7) 1.50 RSI(R – 8.6) 2.01 RSI (R – 11.4)
Metal Desk Maximum Flute Spanability based on SOPRA-ISO thickness $\geq 25.40 \text{ mm } (1.0 \text{ in}) < 35.56 \text{ mm } (1.4 \text{ in}) \\ > 38.10 \text{ mm } (1.5 \text{ in}) \leq 101.60 \text{ mm } (4.0 \text{ in})$	-	66.70 mm (2 5/8 in) 111.10 mm (4 3/8 in)
Compressive Strength	ASTM D 1621	138 kPa (20 psi) 172 kPa (25 psi)
Density	ASTM D 1622	32 kg/m³ (2.0 lb/ft³)
Linear Dimensional Stability	ASTM D 2126	< 0.5 %
Water Absorption	ASTM C 209 ASTM D 2842	< 1.0 % < 3.5 %
Flame Spread*	ASTM E 84	40 - 60
Tensile Strength	ASTM D 1623	35 kPa (> 730 lb/ft²)

<sup>\*</sup>The numerical ratings as determinated by ASTM Test Method E 84 are not intended to reflect hazards presented by this or any other material under actual fire conditions. (All values are nominal)

## STORAGE AND HANDLING

The SOPRA-ISO PLUS TAPERED thermal insulation boards are covered with a waterproof packaging for handling the panels in the manufacturing plant and during transit only.

**SOPRA-ISO PLUS TAPERED** thermal insulation boards must be stored on a flat substrate and sheltered from inclement weather. In addition, the temporary **SOPREMA** applied packaging must be removed to prevent accumulation of condensation.

When short-term outdoor storage is necessary, **SOPRA-ISO PLUS TAPERED** thermal insulation boards must be stacked on skids at least 75 mm (3 in) above the ground, store flat and cover with a waterproof cover such as a canvas tarpaulin.

Refer to PIMA Technical Bulletin No. 109: Storage & Handling Recommendations for Polyiso Roof Insulation at www.polyiso.org.





