



SOPREMA

SOPREMA MIDDLE EAST
P.O. Box 37 1013, Dubai Airport Free Zone
Building E5A - Office 512
Phone: + 97 1 4 609 1661
info@soprema.ae

TECHNICAL DATA SHEET
130815SME1E
(supersedes -)

ALSAN FLASHING

DESCRIPTION

ALSAN FLASHING is a ready-to-use single component polyurethane/bitumen waterproofing resin applied directly onto substrate without a primer.

APPLICATION

For complete specifications and information please consult your local SOPREMA representative.

INSTALLATION

ALSAN FLASHING can be applied with a brush or roller in 2 or 3 layers on a clean and sound substrate. Mix the product thoroughly before usage.

Transitions must be reinforced with **FLASHING REINFORCEMENT**.

ALSAN FLASHING is UV resistant. It can be left exposed without protection. The top coat can also be covered with granules or slate flakes for aesthetic purposes.

Recommended for use on SBS and APP membranes.

HEALTH & ENVIRONMENT

The membrane does not contain any substance that might be detrimental to health or to the environment and complies with generally accepted health standards and Material Safety Data Sheet (MSDS).

QUALITY CONTROL

SOPREMA has always attached the highest importance to quality control. For this reason, we operate an internationally recognized quality system meeting ISO 9001 & ISO 14001 standards, independently monitored and certified.

Single component

Ready-to- use

Can be installed directly over modified bitumen membranes and many other substrates.

Requires no special tools.

Rapid-curing and safe for all details.

Provides long-term maintenance-free protection against water infiltration.



ME_ALSAN_FLASHING.indd

**SOPREMA**

SOPREMA MIDDLE EAST
P.O. Box 37 1013, Dubai Airport Free Zone
Building E5A - Office 512
Phone: + 97 1 4 609 1661
info@soprema.ae

TECHNICAL DATA SHEET
130815SME1E
(supersedes -)

ALSAN FLASHING

PACKAGING

Specifications	ALSAN FLASHING
Physical State	Brown viscous liquid
Packaging	Cans of 3.78 L and 19 L.
Average consumption	0.75 L/m ² per coat.

PROPERTIES

Properties	Standards	ALSAN FLASHING
Density at 25 °C	-	1070 g/L
Solids Content	-	80 %
Flammability	-	FLAMMABLE
Minimum Application Temperature	-	5 °C
Peel Adhesion after Water Immersion	ASTM C836	792 N/m
Drying Time	-	Ready to recoat after 2 hours. Dry: 12 hours (remains tacky to touch)

(All values are nominal)

STORAGE & HANDLING

Storage: 6 months in original container.
Keep away from any source of heat and dampness.

SPECIAL INDICATIONS

Safety instructions

Flammable before curing
Contains isocyanates. Consult Material Safety Data Sheet
Harmful if inhaled
Avoid skin contact
Keep away from sources of ignition – No smoking



ME_ALSAN_FLASHING.indd