

ELASTOPHENE FLAM 25

ELASTOPHENE FLAM 25 is a SBS elastomeric bitumen waterproofing membrane with a glass fleece reinforcement.

Both sides are covered by a thermofusible film.

User application

ELASTOPHENE FLAM 25 is used as a first or second layer under protection in all two-ply elastomeric bitumen waterproofing systems.

All the applications are described in Technical Approvals or **SOPREMA**'s Technical Guidelines in force.

Composition

		ELASTOPHENE FLAM 25
Reinforcement		Glass fleece
Binder		Elastomeric bitumen : blend of selected bitumen and SBS* thermoplastic polymers
Thickness	On overlap	2,6 mm (-5 % ; +5 %)
Topside		Thermofusible film
Underside		Thermofusible film
Overlap		≥ 60 mm
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings (¹) MDV = Manufacturer's Declared Value		

Packaging

		ELASTOPHENE FLAM 25	
Dimensions of the roll		Standard* 7 m x 1 m	Export 10 m x 1 m
Weight of the roll		about 25 kg	about 32 kg
Storage		Upright on pallet with plastic wrapping	
Roll lengths are given with a tolerance of ≤ 1 %. Roll can be cut in two parts. In this case, the shortest length is 2 meters and the total length is equal to the nominal length. Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. Pallets may be stacked to a maximum of two high with separating layer. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.			

*Prevents from the arduousness for roofers on worksite

Characteristics (outside CE marking)

ELASTOPHENE FLAM 25	
Classification of emission for volatile substances in indoor air	A+

Installation

ELASTOPHENE FLAM 25 must be applied only by heat welding or torch-on techniques.

Hot bitumen must not be used in the bonding process.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.

Traceability:

Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 1119
ELASTOPHENE FLAM 25 SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 07 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBFR204 Certificate of Factory Production Control : 1119-CPR-13132, 13133, 13134 (EN 13707). Certificate of Factory Production Control : 1119-CPR-13136, 13137, 13138 (EN 13969).
EN 13707/EN 13969 Membrane composed of modified elastomeric bitumen and a glass fleece reinforcement. Both sides are covered a thermofusible film. Dimensions: 10 m or 7 m x 1 m x 2,6 mm. Applied by torch-on techniques. First or second layer under protection.

Essential characteristics	Performances	Harmonised Technical Specification
Classification for external fire exposure (Note 1)	F_{ROOF} (t1,t2,t3,t4)	EN 13707:2004 + A2:2009
Root resistance	NPD	
Peel resistance of joints (N / 50 mm)	NPD	
Durability Flow resistance at elevated temperature after ageing	90°C	EN 13969:2004
Durability Watertightness after ageing	Conform	
Resistance to static loading – Method B (kg)	5	EN 13707:2004 + A2:2009 EN 13969:2004
Reaction to fire	E	
Watertightness	Conform	
Resistance to impact – Method A (mm)	400	
Shear resistance of joints (N / 50 mm)	≥ 150	
Flexibility at low temperature	-16°C	
Tensile properties : Tensile strength L x T (N / 50 mm) Elongation L x T (%)	≥ 250 x 150 2 x 2	
Resistance to static loading – Method A (kg)	5	
Resistance to tearing (N)	≥ 50	
Dangerous substances (Notes 2 and 3)	Complies	

Note 1 : Since external fire performance depends on the other components of the roof build-up, no performance can be given.

Note 2 : This product does not contain asbestos or tar constituents.

Note 3 : Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristics	ELASTOPHENE FLAM 25
	MLV*
Flow resistance at elevated temperature (EN 1110)	100 °C
Dimensional stability (EN 1107-1)	0,1 %

*MLV = Manufacturer's Limiting Value: Minimum value as started by the manufacturer to be met during testing of type,

internal quality control or external supervision with a confidence level of 95 %