



# LEVELING PATCH

## Paste

**RESISTO**  
SOLUTIONS ÉTANCHÉITÉ  
WATERPROOFING SOLUTIONS  
[www.resisto.ca](http://www.resisto.ca)

TECHNICAL DATA SHEET  
100222RCAN1E  
(supersedes ---)

### DESCRIPTION

The **RESISTO SEAL LEVELING PATCH** for asphalt surfaces is designed to repair medium cracks and joints into asphalt pavement and to level shallow depressions.

The **RESISTO SEAL LEVELING PATCH** protects against water infiltration into asphalt pavement breakdown caused from wear, rain and freezing temperatures.

### APPLICATION CONDITIONS

- Application temperature: 10 °C (50 °F) and above.
- Surface must be clean and dry.

### PACKAGING & COVERAGE

- 3.62 kg pail
- 13.6 kg pail

### GENERAL INSTRUCTIONS

- Surface must be sound and clean. Remove crumbled asphalt or any loose material and clean the surface using a stiff brush or a chisel.
- Designed for cracks in between 1/4 in. (6 mm) to 3/4 in. (20 mm) or shallow depressions.
- For repairs greater than 1 in. (25 mm) in depth, mix equal parts of aggregate (clean sand and crushed stone, or sand only) and **LEVELING PATCH**, adding enough water to obtain about the same consistency as the original product.
- Apply **RESISTO SEAL LEVELING PATCH** using a trowel and let dry.
- Repeat application if needed.

### LIMITATIONS

- Designed for cracks up to 3/4 in. (20 mm) wide. For wider cracks, use **RESISTO SEAL ASPHALT REPAIR**.
- Do not apply product when rain or freezing temperature is expected within the next 24 hours after installation.
- Allow product to cure completely (firm and dry) before applying a **RESISTO SEAL DRIVEWAY SEALER**.
- Not designed to level ruts (uneven surfaces caused by automobiles weight in parking lots) or other wide surfaces.

For further information, consult the Material Safety Data Sheet.

### STORAGE

- Maximum storage temperature: 38 °C (100 °F).
- **Keep from freezing!**
- Shelf life: 2 years in its original packaging.

