

SELECT 180 MOP / COLD

BASE SHEET MEMBRANE



Base/inner ply membrane composed of SBS modified bitumen applied on a non-woven polyester reinforcement, sanded on both sides.

- Excellent resistance to temperature variations
- Excellent tear resistance

PRODUCT PURPOSE

| | | |
|-----------------|------------------|------------------------------------|
| Application | Sealing | |
| Building Part | Roofing | |
| Types of Slope | Very low slope | Negative slope with internal drain |
| Type of Coating | Bitumen membrane | |

PRODUCT CHARACTERISTICS

| | |
|---------------------|------------------------------|
| Technology | SBS polymer modified bitumen |
| Surface | Sand |
| Underface | Sand |
| Reinforcement | Non-woven polyester |
| Installation Method | Glued with hot bitumen |

PACKAGING

| Code | Width | | Length | | Thickness | | Net Area | | Brute Area | | Units (per pallet) |
|-----------------|-------|---|--------|----|-----------|-----|-----------------|----------------|-----------------|----------------|-----------------------|
| | in | m | ft | m | mils | mm | ft ² | m ² | ft ² | m ² | |
| 8 86442 08102 5 | 39 | 1 | 49 | 15 | 90 | 2.2 | 147 | 13.6 | 161 | 15 | 30 |

INSTALLATION

| | |
|---------------------------------|---|
| Storage | Rolls should be stored upright, tape side up. If the products are stored outdoors, cover them with an opaque protective cover after removing the delivery packaging. Can withstand frost, but must be reactivated for 24 hours to at least 10 °C (50 °F) prior to installation. |
| Minimum Application Temperature | 40 °F (4.5 °C) |
| Surface Preparation | The substrate must be clean, dry and free of dust, grease or other contaminants. |
| Recommendations/ Limitations | <p>It is not recommended to install the membrane directly on wood boards. Cover the surface with a suitable panel or an underlayment membrane prior to the installation of the membrane.</p> <p>It is not recommended to use a product containing bitumen directly on softwood boards or flexible polyvinyl chloride.</p> |

