

ALSAN RS CATALYST POWDER

TECHNICAL DATA SHEET 190806SCANE

(supersedes 181121SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFING

BALCONIES

ADDITIONAL EXPERTISE

DESCRIPTION

ALSAN RS CATALYST POWDER is a reactive agent based on dibenzoyl peroxide used to induce curing of all ALSAN RS resin products during membrane application.

Color: ALSAN RS CATALYST POWDER is supplied as a white powder.

APPLICATION

MIXING: Using a slow-speed (200 to 400 rpm) mechanical agitator, thoroughly mix the entire container of resin for two minutes before each use, and prior to pouring off resin into a second container if batch mixing. Catalyze only the amount of material that can be used within 10-15 minutes. Add pre-measured catalyst to the resin component, stir for two minutes and apply to substrate. Refer to individual product data sheets for specific recommendations and requirements for the resin being used.

The amount of catalyst added to ALSAN RS resins varies based on the resin type, weight of the resin and temperature.

A 15 mL ALSAN RS measuring spoon that equals 0.01 kg of ALSAN RS CATALYST POWDER is supplied by Soprema.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

STORAGE AND HANDLING

ALSAN RS CATALYST POWDER is available in prepackaged 0.1 kg (0.2 lb) packets or in 25 kg (55 lb) bags.

Shelf life: 12 months, properly stored in original unopened containers.

Always store closed containers in cool, ventilated and dry location away from flame or ignition sources.

Keep away from rust, iron and copper. Store in the original container protected from direct sunlight.

DANGER: MAY CAUSE FIRE IF STORED UNDER DIRECT SUNLIGHT OR AT TEMPERATURE OVER 30 °C (86 °F).

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ALSAN_RS_CATALYST_POWDER.indd

1/1