



WATERPROOFING

APPLICATIONS

ACCESSORIES

SOPRAMASTIC ALU

TECHNICAL DATA SHEET

APTDS-E-159-01

DESCRIPTION

SOPRAMASTIC ALU is a solvent-based mastic containing SBS synthetic rubber and bitumen. It complements bituminous waterproofing membranes and is used as jointing mastic, caulking material and joint filler. It is compatible with bituminous materials and ensures good waterproofing. It contains leafing aluminium pigmentation providing superior protection against ultraviolet light and its high level of polymer ensures long-term flexibility and elasticity.

APPLICATION

SOPRAMASTIC ALU must be applied to clean, sound substrates. The 310 ml cartridges can be used with a standard cartridge extruder. Excellent adherence on most materials without primer. It can be applied to damp surfaces. To optimise its reflective properties, avoid contact of water until SOPRAMASTIC ALU is dry. SHOULD NOT BE USED AS A PITCH POCKET FILLER.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

| | SOPRAMASTIC ALU |
|-----------|-----------------------|
| Packaging | 310 ml (20 per boxes) |

PROPERTIES

| | SOPRAMASTIC ALU | Test method |
|-----------------------------------|--|-------------|
| Specific Gravity at 20 °C (68 °F) | 1.22 kg/L | - |
| Colour | Aluminium | - |
| Application temperatures Range | -10 to 35 °C (14 to 95 °F) | - |
| Service temperatures Range | -40 to 80 °C (-40 to 175 °F) | - |
| Solids by Weight | 85 % | - |
| Setting time | Between 4 and 24 hours, depending on temperature and quantity applied. | - |

STORAGE AND HANDLING

Shelf life: Up to 36 months in original sealed containers, in cool and ventilated area.
Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.
SOPRAMASTIC ALU is a flammable product. Store in a cool, dry area.

CONSULT THE MATERIAL SAFETY DATA SHEET PRIOR TO USE.

