



INSULATION

APPLICATIONS

WALLS

SOPRA-ISO V PLUS

TECHNICAL DATA SHEET 200514SCANE

(supersedes 190502SCANE)

DESCRIPTION

SOPRA-ISO V PLUS is a closed-cell polyisocyanurate foam insulation board laminated with a non-reflective glass-mat facer on both sides.

SOPRA-ISO V PLUS is used as thermal insulation in SOPREMA's wall systems.

RECOMMENDED SUBSTRATES

This product can be used on most substrates using fasteners or adhesive, such as concrete, wood, wood stud, steel stud, glass-mat gypsum, air/vapour barrier membranes.

APPLICATION

Mechanically fastened (minimum penetration depending on the substrate).

- Fasteners for wood studs 19.0 mm (3/4")
- Fasteners for steel studs 6.5 mm (1/4")
- Fasteners for concrete wall 19.0 à 32.0 mm (3/4" à 1 1/4")

Service temperature: -73 °C to 122 °C (-99 °F to 252 °F)

RESTRICTIONS

SOPRA-ISO V PLUS is not a structural product.

SOPRA-ISO V PLUS must not be left exposed for more than 60 days.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

| Specifications | SOPRA-ISO V PLUS |
|----------------|-----------------------------------|
| Thickness | 13.0 to 102.0 mm (0.5 to 4.0 in)* |
| Dimensions | 1.2 x 2.4 m (4 x 8 ft)* |
| Surface | Non-reflective glass-mat facer |
| Underface | Non-reflective glass-mat facer |

(All values are nominal)

* Other thicknesses and dimensions available upon request.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRA-ISO_V_PLUS.indd

1/2



INSULATION

APPLICATIONS

WALLS

SOPRA-ISO V PLUS

TECHNICAL DATA SHEET 200514SCANE

(supersedes 190502SCANE)

PROPERTIES

SOPRA-ISO V PLUS meets or exceeds the following properties.

| Properties | Standards | SOPRA-ISO V PLUS |
|---|---------------------------------|--|
| Thermal values* 13.0 mm (0.5 in) 19.0 mm (0.75 in) 25.4 mm (1.0 in) 38.1 mm (1.5 in) 50.8 mm (2.0 in) 63.5 mm (2.5 in) 76.2 mm (3.0 in) 89.0 mm (3.5 in) 102.0 mm (4.0 in) | CAN/ULC S704 Type 2, Class 3 | 0.5 RSI (R - 3.0) 0.8 RSI (R - 4.5) 1.1 RSI (R - 6.0) 1.6 RSI (R - 9.0) 2.1 RSI (R - 12.1) 2.7 RSI (R - 15.3) 3.3 RSI (R - 18.5) 3.8 RSI (R - 21.7) 4.4 RSI (R - 25.0) |
| Tensile strength | ASTM D1623 | > 35 kPa (5.08 psi) |
| Flexural strength | ASTM C203 | > 275 kPa (40 psi) |
| Water vapour permeance | ASTM E96 (method A) | > 60.0 ng/Pa•s•m ² at 25.4 mm (≤ 1.05 perm at 1 in) |
| Water absorption | ASTM D2842 | < 3.5 % by volume (typically < 0.6 % by volume) |
| Dimensional stability at -29 °C (-20 °F), ambient humidity at 80 °C (176 °F), ambient humidity at 70 °C (158 °F), 97 % relative humidity | ASTM D2126 | < 0.5 % |
| Flame spread | CAN/ULC S102 | > 25 < 500 |
| Flame spread | ASTM E84 | < 75 |
| Smoke development | ASTM E84 | < 450 |

* Conditioned thermal values were determined by ASTM Test Method C518 at 23.9 °C (75 °F) mean temperature. Test specimens were conditioned in accordance with procedures outlined in CAN/ULC S704.

(All values are nominal)

* LTTR value for SOPRA-ISO V PLUS is 5.7 for 25.4 mm (1 inch).

STORAGE AND HANDLING

SOPRA-ISO V PLUS panels are covered with a waterproof packaging for handling the panels in the manufacturing plant and during transit only.

When short-term outdoor storage is necessary SOPRA-ISO V PLUS panels must be stacked on skids at least 75 mm (3 in) above the ground, store flat and cover with a waterproof cover such as a canvas tarpaulin. In addition, the temporary SOPEMA applied packaging must be removed to prevent accumulation of condensation.

Refer to PIMA Technical Bulletin No. 109: Storage and Handling Recommendations for Polyiso Roof Insulation at www.polyiso.org.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRA-ISO_V_PLUS.indd

2/2