



COMPLEMENTARY PRODUCTS

APPLICATIONS

BRIDGES

ANTIROCK EMULSION PRIMER

TECHNICAL DATA SHEET 160831SCANE

(supersedes 160516CANE)

DESCRIPTION

ANTIROCK EMULSION PRIMER is a bituminous emulsion (stabilized blend of bitumen and water without solvent). It is used to prime concrete and metal surfaces on civil engineering structures in order to improve the adhesion of ANTIROCK waterproofing membranes.

APPLICATION

ANTIROCK EMULSION PRIMER can be applied with a brush, roller or sprayer (the Airless process is not suitable) on clean, dry substrates free of any residue that may hinder adherence.

It must be thoroughly dry before applying the waterproofing membrane. Drying time will vary depending on air and surface temperature and humidity.

Average coverage: 0.15 to 0.25 L/m² depending on surface porosity. A 19L pail will cover about 100 m² (1 075 pi²).

Minimum application temperature: 5 °C (41 °F).

RESTRICTION

ANTIROCK EMULSION PRIMER is not ruled by hazardous materials transport regulations.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	ANTIROCK EMULSION PRIMER
Specific Gravity at 20 °C	1.00 kg/L
Colour (Color)	Dark Brown
Packaging	19 L (5 gal.)
Solids by Weight	44 %
Brookfield Viscosity, 25 °C	675 cP
Flash point, ASTM D93 (°C)	N/A – NON-FLAMMABLE

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ANTIROCK_EMULSION_PRIMER.indd



COMPLEMENTARY PRODUCTS

APPLICATIONS

BRIDGES

ANTIROCK EMULSION PRIMER

TECHNICAL DATA SHEET 160831SCANE

(supersedes 160516CANE)

CLEANING

Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

STORAGE AND HANDLING

Storage temperature: 0 to 40 °C.

Shelf life: Up to 12 months in original sealed containers, in cool and ventilated area.

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ANTIROCK_EMULSION_PRIMER.indd

2/2