

COLPHENE BSW H

COLPHENE BSW H is a high-performance flexible SBS elastomeric bitumen waterproofing membrane with a non-woven polyester reinforcement. The topside is coated with specially engineered carbon dioxide crystals and the underside is covered by a thermofusible plastic film.

Thanks to its special formulation and composition **COLPHENE BSW H** has excellent, continuous and homogenous bond to poured structural concrete, increased resistance to hydrostatic pressure and superior resistance to tears and punctures.

Its unique design, including the **DUO SELVEDGE** technology, allows welding of side laps using a torch or a hot air gun.

User application

COLPHENE BSW H is designed for horizontal blind side waterproofing applications (below grade and tanking works).

All the applications are described in **SOPREMA's** Technical Guidelines in force.

Composition

	COLPHENE BSW H
Reinforcement	Non woven polyester
Binder	Elastomeric bitumen : blend of selected bitumen and SBS* thermoplastic polymers
Thickness (EN 1849-1)	3,5 mm (-5% ; +5%)
Weight (EN 1849-1)	4,3 kg/m ²
Topside	Specially engineered carbon dioxide crystals
Underside	Thermoplastic plastic film
Overlap (DUO technology)	100 mm (55 mm sticky bitumen + 45 mm thermofusible film)
*According to UEAtc directives concerning the normalization of waterproof elastomeric SBS bitumen coverings	

Packaging

	COLPHENE BSW H
Dimensions of the roll	10 m x 1 m
Weight of the roll	about 43 kg
Storage	Rolls must be stored upright, with the selvedge side on top. If the product is stored outdoors, cover them with an opaque protective cover after removal of the delivery packaging
Roll lengths are given with a tolerance of < 1 %. Width of roll is given with a tolerance of 1% (UEAtc). Rolls must be stored upright on flat ground. During storage, protect the rolls against moisture. In cold weather, we recommend that the rolls be kept at a minimum temperature of + 2°C (+ 36 °F) for at least 5 hours before installation.	

Characteristics (outside CE marking)

	COLPHENE BSW H
Peel or stripping strength of adhesive bonds Bonding peel strength (ASTM D 903-98 // 2010)	average 3400 N / m
Resistance to hydrostatic head (ASTM D5385)	≥110 m (≥360 ft)
Lateral water migration (ASTM D5385 modified)	≥110 m (≥360 ft)

Installation

COLPHENE BSW H is installed loose laid on the concrete slab or compacted soil.

To prevent overly thick membranes, stagger the end laps by a minimum of 300 mm.

Side lap joints must be a minimum of 100 mm and end lap joints must be a minimum of 150 mm. Membrane overlaps are torched-on.

All angles changes (inside and outside corners) and others details must be reinforced by heat-welding on additional 300 mm piece of **COLPHENE BSW H** centered on the angle.

It is recommended to install **COLPHENE BSW PROTECT'R**, as a protection layer, over the **COLPHENE BSW H** prior to placement of the reinforcement steel bars and pouring of the concrete slab.

DUO SELVEDGE

Over the entire width of **DUO SELVEDGE**, 55 mm of the surface is covered with exposed sticky bitumen. The remaining surface of the selvedge (45 mm) is covered by a thermofusible plastic film to seal overlap by torch-on techniques.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

Special indications

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For further information, please refer to relevant Safety Data Sheet.

Traceability:

Product traceability is ensured through a manufacturing code present on the packaging.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.

CE marking

 1119 COLPHENE BSW H
SOPREMA 14 rue de Saint-Nazaire – CS 60121 67025 STRASBOURG cedex 14 Construction Product Regulation (CPR) Declaration of Performance : DoP n° WPBEX250 Certificate of Factory Production Control: 1119-CPR-13136, 13137, 13138 (EN 13969)
EN 13969 Membrane composed of modified elastomeric bitumen and non-woven polyester reinforcement. Topside is coated with specially engineered carbon dioxide crystals and the underside is covered with a thermofusible film. Dimensions 10 m x 1 m x 3,5 mm. Must be loose laid. For below grade and tanking works.

Essential characteristics	Performances	Harmonised Technical Specification
Reaction to fire (EN 13501-1)	E	EN 13969:2004 + A1:2006
Root resistance (EN 13948)	NPD	
Peel resistance of joints (N / 50 mm) (EN 12316-1)	≥ 100	
Watertightness (EN 1928)	Conform	
Resistance to impact – Method A (mm) (EN 12691) Method A is on rigid substrate (aluminium)	1000	
Shear resistance of joints (N / 50 mm) (EN 12317-1)	≥ 700	
Flexibility at low temperature (EN 1109)	≤ -16°C	
Tensile properties: (EN 12311-1) Tensile strength L x T (N / 50 mm) Elongation L x T (%)	800 (±100) x 800 (±100) 40 (±10) x 40 (±10)	
Resistance to static loading (kg) Method B (EN 12730) Method B is on rigid substrate (concrete)	10	
Resistance to tearing (nail shank) L x T (N) (EN 12310-1)	250 (±50) x 250 (±50)	
Durability (EN 1296 / EN 1928) Watertightness after ageing	Conform	
Dangerous substances (Notes 2 and 3)	Complies	

Note 2: This product does not contain asbestos or tar constituents.

Note 3: Since there is no European test method available, no performance declaration for leaching behavior can be made. It must be made according to national rules in force in the place of use.

Additional characteristic	COLPHENE BSW H
Durability (EN 1296 / EN 1110) Flow resistance at elevated temperature after ageing	≥ 90°C