



WATERPROOFING

APPLICATIONS

ROOFING

# LASTOBOND SHIELD HT

TECHNICAL DATA SHEET ANZ-TDS-38-LASTOBOND SHIELD HT

## DESCRIPTION

LASTOBOND SHIELD HT is a self-adhesive roof underlayment and eave protection membrane composed of SBS modified bitumen with a glass mat reinforcement. The surface is slip resistant tri-laminate woven polyethylene, while the underface is covered with a "split-back" silicone release film. This surface allows the use of LASTOBOND SHIELD HT membrane on various slopes.

## RECOMMENDED SUBSTRATES

This product can be used on plywood, OSB or asphaltic boards such as SOPRABOARD.

## SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. In a case where a special job site condition requires superior adhesion, using one of ELASTOCOL STICK primer is recommended.

## INSTALLATION

LASTOBOND SHIELD HT is used under roofing shingles. The thermal resistance of LASTOBOND SHIELD HT allows the use of the membrane under roof covering materials (metal claddings, tiles, etc.) which can reach high temperatures. It is advisable to install the roof covering materials within 24 hours after the installation of those membranes.

### SELF-ADHESIVE

LASTOBOND SHIELD HT must be adhered to support by peeling off the siliconed release film. Once installed, a pressure must be applied over the whole surface using a membrane roller to ensure good contact.

Application temperatures : applications  $\geq 10$  °C (50 °F)

Service temperatures : LASTOBOND SHIELD HT - applications between -45 to 115 °C (-49 to 239 °F)

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

Specifications	LASTOBOND SHIELD HT
Thickness	1.0 mm (40 mil)
Dimensions	22.9 x 0.91 m (75 x 3 ft)
Weight	0.97 kg/m <sup>2</sup> (0.2 lb/ft <sup>2</sup> )
Selvedge width	75 mm (3 in)
Surface	Tri-laminate woven polyethylene
Underface	Self-adhesive, covered with a "Split-back" silicone r elease film
Rolls per skid	36

(All values are nominal)



# LASTOBOND SHIELD HT

TECHNICAL DATA SHEET ANZ-TDS-38-LASTOBOND SHIELD HT

## PROPERTIES

Properties	Standards	LASTOBOND SHIELD HT
Breaking Strength, MD/XD	ASTM D1970	11.3 / 15.4 kN/m (64 / 88 lbf/in)
Elongation at Break, MD/XD	ASTM D1970	52 / 24 %
Tear resistance, MD/XD	ASTM D1970	375 / 400 N (84 / 90 lb)
Static puncture resistance	ASTM D5602	400 N (90 lbf)
Adhesion to plywood, 4.5 °C (40 °F)	ASTM D1970	500 N/m (34.3 lbf/ft)
Adhesion to plywood, 24 °C (75 °F)	ASTM D1970	1100 N/m (75.4 lbf/ft)
Low temperature flexibility	ASTM D1970	Pass at -30 °C (-22 °F)
Water vapour permeance	ASTM E96	1.25 ng / Pa•s•m <sup>2</sup> (0.022 perm)
Nail Sealability	ASTM D1970	Pass

(All values are nominal)

## STORAGE & HANDLING

Rolls must be stored upright, with the selvedge side on top. If the product is stored outdoors, cover them with an opaque protective cover after the removal of the delivery packaging.

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative or the contractor is responsible for checking the suitability of products for their intended use.

Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by Soprema Australia Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Soprema Australia Pty Ltd are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	LASTOBOND SHIELD HT
Initial Issue	30.10.2019
Amendment	
Author	JJ