



WATERPROOFING

APPLICATIONS

ROOFING

EXTERIOR WALL

STRATEC II

TECHNICAL DATA SHEET ANZ-TDS-46-STRATEC IITRATEC II

DESCRIPTION

STRATEC II is a versatile and resistant synthetic very highly breathable screen (vapour permeable) used as roof tile underlay in ventilated or non-ventilated slated pitched roof. It will also prevent the ingress of wind-blown rain, dust or snow.

STRATEC II is also used as rain barrier (underlay for walls).

COMPOSITION

	STRATEC II
Reinforcement	Very highly breathable polypropylene foil
Weight (EN 1849-2)	145 g/m ²
Thickness (EN 1849-2)	0,60 mm
Upperface	Non-woven polypropylene foil
Underface	Non-woven polypropylene foil

CHARACTERISTICS

	STRATEC II MDV*
Tensile Strength (EN 12311-1)	
-longitudinal	290 N/ 5 cm (250)
-transverse	220 N/ 5 cm (200)
(After ageing test)	
Elongation (EN 12311-1)	
-longitudinal	77 % (47)
-transverse	83 % (54)
(After ageing test)	
Resistance to tearing (nail shank) (EN 12310-1)	
-longitudinal	175 N
-transverse	230 N
Resistance to watertightness (EN 1928) Before and after ageing test	W1 Class
Water vapour transmission (EN 1931)	Sd = 0.045 m
Low temperature flexibility (EN 1109)	-20°C
Dimensional stability (EN 1107-2)	< ± 0.5%
EST Classification (French standard) for roof tile underlay	E1Sd1TR2
Air permeability (EN 12114)	0.026m3/(m ² .h) at 50Pa
Reaction to fire (EN 13501-1)	E Class

(*)MDV = Manufacturer's determined value : An arithmetic mean value of a minimum number of independent measurements.





WATERPROOFING

APPLICATIONS

ROOFING

EXTERIOR WALL

STRATEC II

TECHNICAL DATA SHEET ANZ-TDS-46-STRATEC IITRATEC II

PACKING

	STRATEC II
Roll dimensions	50 m x 1,50 m (75 m ²)
Roll weight	11.50 kg
Colour	Light grey anti slip upperface, white anti slip underface for an easier application
Storage	Upright on pallet with plastic wrapping, protected against moisture

USER APPLICATION

This underlay will be installed and fixed according to Technical Guidelines:

On rafters with corrosion-resistant staples or galvanized clout nails as appropriate.

Either secured to the support with counter battens at least 12 mm thick to create a drainage and vapour dispersal space between the product and the tiles.

May be used over sarking boards of softwood and either with continuous insulation or insulation placed between the rafters.

Maximum rafter spacing : 60 cm.

Minimum overlaps : 10 cm (20 cm for <20% slope).

INSTALLATION

STRATEC II installation can be carried out easily by slaters / tilers experienced with this type of product.

It may be used as temporary waterproofing during 8 days.

SPECIAL INDICATION

Hygiene, health and environment:

The product does not contain any substance likely to be detrimental to health or to environment and complies with generally admitted Health and Safety Requirements. For more information, please refer to relevant Safety Data Sheet.

Quality control:

SOPREMA has always attached the highest importance to Quality Control.

For this reason, we operate an independently monitored Quality Assurance System in compliance with **BS EN ISO 9001:2000**, certified by **BSI**

Management System.

CE MARKING

STRATEC II complies with **EN 13859-1** and **EN 13859-2** with the **CE** marking.



STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative or the contractor is responsible for checking the suitability of products for their intended use.

Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by Soprema Australia Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Soprema Australia Pty Ltd are responsible for carrying out procedures appropriate to a specific application.

DOCUMENT CONTROL	
Product	STRATEC ii
Initial Issue	30.10.2019
Amendment	
Author	JJ

