



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFING

BALCONIES

ADDITIONAL EXPERTISE

ALSAN RS 233 SELF-LEVELING MORTAR

TECHNICAL DATA SHEET 200827SCANE

(supersedes 190508SCANE)

DESCRIPTION

ALSAN RS 233 SELF-LEVELING MORTAR is a two-component polymethyl methacrylate-based (PMMA) self-leveling mortar. ALSAN RS 233 SELF-LEVELING MORTAR is used to level rough surfaces in conjunction with ALSAN RS systems. ALSAN RS 233 SELF-LEVELING MORTAR is composed of ALSAN RS 210 resin and ALSAN RS 223 Cementitious Powder.

COLOUR: ALSAN RS 233 SELF-LEVELING MORTAR is supplied in a standard colour of Pebble Grey.

SURFACE PREPARATION

Surface must be dry, clean and free of loose particles, formwork, curing products, irregularities, slurry, etc.

APPLICATION

MIXING: Using a slow-speed (200 to 400 rpm) mechanical agitator, thoroughly mix the entire container of ALSAN RS 210 resin for two minutes before each use. Into a larger container, slowly add ALSAN RS 223 Cementitious Powder to resin while mixing; continue mixing for 2 to 5 minutes.

Mixing ratio of ALSAN RS 210 resin is one pail (10 kg (22 lbs)) to one bag (23 kg (50.7 lb)) of ALSAN RS 233 Cementitious Powder. Catalyze with ALSAN RS CATALYST, only the amount of resin that can be used within 10-15 minutes.

Add pre-measured ALSAN RS CATALYST to the resin component, stir for two minutes and apply to substrate. The amount of catalyst added should be based ONLY on the weight of the ALSAN RS 210 resin used, and not the entire batch (resin + filler) weight.

Refer to Catalyst Mixing Chart for additional information.

CATALYST MIXING CHART

SUMMER FORMULATION			
Temperature range	Catalyst activation	kg	tbsp*
Catalyst dosage per 10 kg container of resin used			
5 °C to 10 °C (41 °F to 50 °F)	4 %	0.40	40
10 °C to 35 °C (50 °F to 95 °F)	2 %	0.20	20
Catalyst dosage per each 1 liter (1.2 kg) of resin used			
5 °C to 10 °C (41 °F to 50 °F)	4 %	0.04	4
10 °C to 35 °C (50 °F to 95 °F)	2 %	0.02	2

WINTER FORMULATION			
Temperature range	Catalyst activation	kg	tbsp*
Catalyst dosage per 10 kg container of resin used			
-5 °C to 8 °C (23 °F to 46 °F)	4 %	0.40	40
8 °C to 15 °C (46 °F to 59 °F)	2 %	0.20	20
Catalyst dosage per each 1 liter (1.2 kg) of resin used			
-5 °C to 8 °C (23 °F to 46 °F)	4 %	0.04	4
8 °C to 15 °C (46 °F to 59 °F)	2 %	0.02	2

* Each 0.01 kg of ALSAN RS CATALYST POWDER equals approximately to a level 1-tablespoon size scoop (15 mL ALSAN RS Measuring Spoon) supplied by Soprema.

APPLICATION: After mixing, apply resin to clean and prepared substrate at the required consumption using rollers or notched squeegee. The resin should be spread evenly into the surface. See individual system specifications for specific guidelines regarding application of primer, membrane, topcoat and/or slip-resistant protective surfacing.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ALSAN_RS_233_SELF_LEVELING_MORTAR.indd



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFING

BALCONIES

ADDITIONAL EXPERTISE

ALSAN RS 233 SELF-LEVELING MORTAR

TECHNICAL DATA SHEET 200827SCANE

(supersedes 190508SCANE)

REACTION TIMES

	SUMMER FORMULATION	WINTER FORMULATION
	Ambient temperature : 20 °C (68 °F)	
Pot life	15 minutes	20 minutes
Rain proof after	30 minutes	45 minutes
Set time / walked on / next layer	60 minutes	90 minutes
Fully cured	3 hours	6 hours

Pot life is dependent on ambient temperatures and will be reduced at higher temperatures. Minimum set times are approximate and may vary. Actual set times and cure times should be established in the field, based on actual field conditions.

COVERAGE

SUBSTRATE PROFILE	CONSUMPTION ² PER 33 KG UNIT m ² (ft ²)	TOTAL THICKNESS mm (mil)
Smooth to CSP ¹ 3	7.4 (80)	2.0 (79)
CSP ¹ 4	7.2 (77)	2.1 (83)
Rough to CSP ¹ 5	6.9 (74)	2.2 (87)

1- CPS : Concrete Surface Profile

2- Coverage rates are approximate and may vary depending on substrate conditions and the application technique. The above data may vary by +/- 10%.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

ALSAN RS 233 SELF-LEVELING MORTAR resin is supplied in two parts:

ALSAN RS 210 resin is supplied in a 10 kg (22 lb) resealable container with locking ring.

ALSAN RS 223 Cementitious Powder is supplied in a 23 kg (50.7 lb) bag.

STORAGE AND HANDLING

Shelf life: 12 months, properly stored in original unopened containers.

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_ALSAN_RS_233_SELF_LEVELING_MORTAR.indd