







APPLICATIONS

ROOFS

FOUNDATIONS CIVIL WORKS

IZ-TDS-11-ANTIROCK PRIMER

TECHNICAL DATA SHEET

DESCRIPTION

ANTIROCK PRIMER is a blend of SBS modified bitumen, fast-evaporating solvents and adhesive enhancing additives.

ANTIROCK PRIMER is used to prime concrete and metal surfaces to improve the adhesion of SOPREMA bituminous torch-on membranes.

INSTALLATION PROCEDURE

- ANTIROCK PRIMER can be applied with a brush or roller on clean, dry substrates free of any residue that may hinder adherence. Shake well before using.
- It must be thoroughly dry before applying the waterproofing membrane. Drying time will vary depending on air and surface temperature and humidity.

WARNING: Do not accelerate drying of ANTIROCK PRIMER by heating with a torch.

CLEANING

• Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

RESTRICTION

- ANTIROCK PRIMER is a highly flammable product.
- Store away from direct sunlight and open flame. Keep ignition sources away during application and until solvent has evaporated.
 Harmful if inhaled, swallowed or when in contact with the skin. In closed areas, ventilate carefully using mechanical means if necessary.
- · Do not pour residues in drains.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE

PACKAGING

| SPECIFICATIONS | ANTIROCK PRIMER |
|------------------|-------------------|
| Physical state | Liquid |
| Colour | Brown |
| Coverage | 0.15 to 0.25 l/m² |
| Packaging | 19 l |
| Pails per pallet | 36 |













ACCESSORY PRODUCTS

APPLICATIONS

ROOFS

FOUNDATIONS

CIVIL WORKS

PROPERTIES

| PROPERTIES | ANTIROCK PRIMER |
|----------------------------------|-----------------|
| Specific gravity at 20°C | 0.91 kg/l |
| Solids by weight | 35 % |
| Brookfield Viscosity, 25 °C | 50 cP |
| Flash point, ASTM D93 | -3 °C |
| Drying time on smooth surfaces * | Minimum 1 hour |

(All values are nominal)

STORAGE AND HANDLING

Shelf life: Up to 5 years in original sealed containers, in cool and ventilated area.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor are responsible for checking the suitability of products for their intended use.

Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by Soprema Australia Pty Ltd either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they are responsible for carrying out procedures appropriate to a specific application.







^{*} In all cases, drying time must allow complete evaporation of solvents.