

FLAGON SR

TECHNICAL DATA SHEET



ANZ-TDS-34-FLAGON SR



WATERPROOFING

APPLICATIONS

ROOFS

GREEN ROOFS

PLANTER BOXES

DESCRIPTION

FLAGON SR is a synthetic PVC-P membrane obtained by cast process with a polyester reinforcement mesh and a signal layer on the surface.

FLAGON SR is design for roofing applications. It is resistant to ultraviolet rays, to puncturing, to weathering and to roots growth.

Flagon PVC membranes are naturally fire resistant, they self-extinguish and resist the spread of flame.

FIELD OF APPLICATION

Designed for single-ply application on horizontal surfaces, FLAGON SR is mechanically fixed on insulation panels, concrete ceilings or existing waterproofing with separation layer covering for the following general applications:

- General roofing
- Green roofs
- Planter boxes
- Plaza decks
- Balconies

APPLICATION METHOD

On the main surface, FLAGON SR is semi-loose laid by mechanical fastening, and always laid to run a few centimetres on the parapet. FLAGON SR membrane is fastened around the perimeter of the roof and around any protruding features with FLAGORAIL bars or adapted screws and plates.

At the top of the upstands, FLAGON SR is heat welded on FLAGMETAL strip mechanically fastened onto the substrate.

The overlaps are heat welded using a leister automatic welder or a hot air gun.

INSTALLATION PROCEDURE

SUBSTRATE

- No work should start until all surfaces are smooth, dry, and free of ice, snow or any other substance that may prevent the membrane from adhering properly.
- Substrate must have a minimum 1% gradient to ensure that water drains to drainage outlets.
- Concrete substrate must be fully cured before application of the membrane.
- Concrete substrate must have a Concrete Surface Profile (CSP) between 2 and 4 as per International Concrete Repair Institute.
- Adhesion test is recommended prior to installation of membrane.
- Commencement of installation shall be taken as acceptance of the substrate by the Applicator.
- The use of FLEXOCOL V is required before the installation of FLAGON SR or FLAGON SV membrane at the vertical.

INSTALLATION

- Unroll membrane sheets onto the roof surface.
- Ensure specified side-laps and end-laps are maintained. End-laps should be staggered 1 m apart or lay a transverse sheet or strip (minimum width 20 cm) across the bottom of two or more perfectly aligned and parallel sheets to provide a connection to the subsequent set.
- Upstands are waterproofed with FLAGON SR or FLAGON SV membrane using FLEXOCOL V adhesive for upstands > 40 cm high or mechanical fixed when upstands < 40 cm.

Compliance with AS 4654.1

Service life in excess of 35 years

Cold applied, flameless solution

Resistant to wind stress

High resistant to weathering & UV rays

Self-extinguish



SOPREMA.COM.AU • +61 (3) 9221 6230

FLAGON SR



WATERPROOFING

APPLICATIONS

ROOFS

GREEN ROOFS
PLANTER BOXES

TECHNICAL DATA SHEET

ANZ-TDS-34-FLAGON SR

INSTALLATION (CONT.)

- Laying of FLAGON SR strips to be positioned at the head of the rolls of FLAGON SR membrane; the strips should be welded in order to join the heads of the rolls of FLAGON SR.
- All penetrations and upturn details should be waterproof as per SOPREMA Installation Guides and detail drawings.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

SPECIFICATIONS	FLAGON SR	
Thickness	1.5 mm	2 mm
Roll dimensions	20 m x 2.10 m	20 m x 2.10 m
Roll weight	82 kg	101 kg
Rolls per pallet	14	14

PROPERTIES

PROPERTIES	STANDARDS	FLAGON SR	
		1.5 mm	2 mm
Weight (kg/m ²)	EN 1849-2	1.80	2.40
Tensile strength (N/5cm)	EN 12311-2	≥ 1100	≥ 1100
Elongation to break (%)	EN 12311-2	≥ 15	≥ 15
Tear resistance (N)	EN 12310-2	≥ 200	≥ 200
Resistance to impact (mm)	EN 12691	≥ 800	≥ 1250
Cold bending (°C)	EN 495-5	≤ - 25	≤ - 25
Hydrostatic pressure resistance (6 hours at 0.5 Mpa)	EN 1928 met. B	waterproof	waterproof
Dimensional stability after 6 hours at 80°C (%)	EN 1107-2	≤ 0.5	≤ 0.5
Resistance to artificial weathering (UV)	EN 1297	no surface cracking	no surface cracking
Resistance to roots penetration	EN 13948	no penetration	no penetration
Resistance to static punching (kg)	EN 12730	≥ 20	≥ 20
Fire resistance	EN ISO 11925-1 EN 13501-1	E	E

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor are responsible for checking the suitability of products for their intended use.



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS_FLAGON_SR_10-2020_RA

2/2