

SOPRASUN PLUS 3 / PLUS 3 P



WATERPROOFING

APPLICATIONS

ROOFS

FOUNDATIONS

PLAZA DECKS

TECHNICAL DATA SHEET

ANZ-TDS-03-SOPRASUN PLUS 3/3P

DESCRIPTION

SOPRASUN PLUS 3 is an APP-modified bitumen waterproofing membrane designed for roofing and below grade applications.

SOPRASUN PLUS 3 is reinforced with a non-woven polyester combine with fiberglass. The composite reinforcement conveys good mechanical characteristics, excellent dimensional stability, and elastic performance.

SOPRASUN PLUS 3 SANDED top surface is coated with anti-adhesive amorphous sand; bottom surface is covered with a thermofusible plastic film.

SOPRASUN PLUS 3 PLAIN top and bottom surface are covered with a thermofusible plastic film.

Compliance with AS 4654.1

Good mechanical properties

Excellent dimensional stability

Excellent elastic performance

Wide temperature tolerance

FIELD OF APPLICATION

Suitable as a top layer (no UV exposure) and as an under layer in multi-layer waterproofing assemblies, SOPRASUN PLUS 3 is used in vertical and horizontal waterproofing for the following general applications:

- Rooftops
- Plaza decks
- Balconies
- Planter boxes (in conjunction with SOPRAGUM PLUS GARDEN 4)
- Retaining Walls

APPLICATION METHOD

SOPRASUN PLUS 3 can be fully heat welded using a propane torch, MINI MACADEN machine or mechanically fixed (only when used as under layer in multi-layer roofing assemblies).

INSTALLATION PROCEDURE

SUBSTRATE

- No work should be started until all surfaces are smooth, dry and free of ice, snow or any other substance that may prevent the membrane from adhering properly
- Substrate must have a minimum 1% gradient to ensure that water drains to drainage outlets
- Do not install heat welded membranes directly onto combustible substrate
- Concrete substrate must be fully cured before application of the membrane
- Concrete substrate must have a Concrete Surface Profile (CSP) between 3 and 6 as per International Concrete Repair Institute
- Adhesion test is recommended prior to installation of membrane
- Commencement of installation shall be taken as acceptance of the substrate by the Applicator

PRIMING

- When installed as top layer over base sheet membrane, a primer is not required
- When installed over concrete or metal surface prime with ANTIROCK PRIMER at the rate specified in TDS



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS_SOPRASUN_PLUS_3

1/3

SOPRASUN PLUS 3 / PLUS 3 P



WATERPROOFING

APPLICATIONS

ROOFS

FOUNDATIONS

PLAZA DECKS

TECHNICAL DATA SHEET

ANZ-TDS-03-SOPRASUN PLUS 3/3P

INSTALLATION PROCEDURE (CONT.)

HEAT WELDING

- Unroll membrane sheets onto the roof surface
- Starting at the low point of the roof, lay out the membrane to ensure the plies are installed perpendicular to the roof slope, shingled to prevent back-water laps
- Ensure specified side-laps and end-laps are maintained. End-laps should be staggered 1m apart.
- As the membrane ply is unrolled, apply heat to the underside of the ply until the thermofusible film melts sufficiently for full adhesion to the substrate, and full adhesion between plies
- For hand-held roof torches, continuously move the torch side-to-side across the underside of the roll to melt the bitumen while continuously unrolling sheet. While unrolling and heating the sheet, ensure approximately 6 to 12mm of hot bitumen flows ahead of the roll, and there is 3 to 6mm bleed out at all laps. Ensure all side-laps are fully adhered and sealed watertight.
- Adjust application methods to accommodate varying environmental conditions as necessary to achieve the desired results
- At the 150mm end-laps ensure a fully adhered watertight seal. Melt the thermofusible film or embed granules and remove other membrane surfacing, where present, using a torch or hot-air welder.
- All penetrations and upturn details should be waterproof as per SOPREMA Installation Guides and detail drawings

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

SPECIFICATIONS	SOPRASUN PLUS 3 SANDED	SOPRASUN PLUS 3 PLAIN
Thickness	3 mm	3 mm
Roll dimensions	10 m × 1 m	10 m × 1 m
Roll weight	36 kg	30 kg
Rolls per pallet	25	25

(All values are nominal)

PROPERTIES

PROPERTIES	TEST METHOD	SOPRASUN PLUS 3 SANDED	SOPRASUN PLUS 3 PLAIN
Abrasion resistance*	AS 1580.403.2	NPD*	NPD*
Bond strength to concrete	ASTM C794	27.4 N/2.5cm	
Cyclic movement	CSIRO Moving joint test (B)	PASS	
Dimensional stability	ASTM D5147	MD: -0.10 % ; CD: -0.19%	
Elongation at break	AS 4654.1	37 %	
Field seam strength	ASTM D1876	1.2 (±162) N/m	
Heat ageing	AS 4654.1 (AS 1145.3)	PASS ; no visual change	
Ultraviolet resistance*	AS 4654.1 (AS 1145.3)	NPD*	
Heat resistance	(ASTM D4799)	NPD*	
Tensile strength	ASTM D5147	740 N/5CM	
Durability	AS 4654.1	PASS	
Watertightness	EN 1928-B:2000	> 200 kPa	
Water vapor transmission rate	AS 4654.1	0 perm**	

* Applicable only to self - protected ** The results values are below the variation of the equipment. We consider that the sample have no water vapor transmission



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS_SOPRASUN_PLUS_3_RA

2/3

SOPRASUN PLUS 3 / PLUS 3 P



WATERPROOFING

APPLICATIONS

ROOFS

FOUNDATIONS

PLAZA DECKS

TECHNICAL DATA SHEET

ANZ-TDS-03-SOPRASUN PLUS 3/3P

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor are responsible for checking the suitability of products for their intended use.



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS_SOPRASUN_PLUS_3_09-2021RA

3/3