



ACCESSORY  
PRODUCTS

APPLICATIONS

WALLS

ROOFS

# SOPRASEAL SEALANT S37S

TECHNICAL DATA SHEET

ANZ-TDS-110-SOPRASEAL SEALANT S37S

## DESCRIPTION

SOPRASEAL SEALANT S37S is a low VOC, solvent-free, polyether adhesive-sealant. This fast-setting, moisture curing product is designed to be applied on most substrate without the need of primer.

SOPRASEAL SEALANT S37S provide strong and elastic bonds on most of construction materials as well as all SOPRASEAL membranes. SOPRASEAL SEALANT S37S can be applied at temperatures range from 10°C to 40°C with a pneumatic cartridge (no special tools or mixers required).

SOPRASEAL SEALANT S37S will not shrink upon curing or discolver when left exposed to UV. SOPRASEAL SEALANT S37S is fast setting and after 7 days is fully cured.

Solvent free

UV exposure up to 180 days

No primer required

Compatible with most substrates

## INSTALLATION PROCEDURE

### APPLICATION:

- SOPRASEAL SEALANT S37S must be applied to clean, sound substrates
- SOPRASEAL SEALANT S37S tubes can be used with a standard cartridge extruder as an accessory sealant to all SOPRASEAL membranes.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

SPECIFICATIONS	SOPRASEAL SEALANT S37S
Physical state	Viscous
Colour	Gray or White
Container	600 mL
Units per Pallet	1200

## PROPERTIES

PROPERTIES	SOPRASEAL SEALANT S37S
Surface drying time	15-40min
Hardness Shore A	≥ 40
Tension strength	≥ 2.0 MPa
Shear strength	≥ 1.5 MPa
Elongation at break	≥ 400%
Curing speed	4.0 mm/d



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS\_SOPRASEAL\_SEALANT\_S37S\_08-2022\_RA

1/2

# SOPRASEAL SEALANT S37S



ACCESSORY  
PRODUCTS

APPLICATIONS

WALLS

ROOFS

TECHNICAL DATA SHEET

ANZ-TDS-110-SOPRASEAL SEALANT S37S

## STORAGE AND HANDLING

Store unopened containers in a cool, dry area. Protect from water, heat and direct sunlight. Extreme temperatures will reduce shelf life. Temperature should be 10-25°C. Shelf life: 9 month

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor are responsible for checking the suitability of products for their intended use.



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS\_SOPRASEAL\_SEALANT\_S37S\_08-2022\_RA

2/2