

ALSAN 172

TECHNICAL DATA SHEET APTDS-E-68-01

DESCRIPTION

ALSAN 172 is a PMMA based fast-curing primer for asphalt substrates in preparation for the later application of ALSAN PMMA resins.

MATERIAL

2-component, fast-curing and flexible PMMA-based (polymethyl methacrylate) primer.

PROPERTIES

- Excellent adhesion to asphalt substrates
- Easy to apply
- Can also be applied at sub zero temperatures
- Fast-curing
- Hydrolysis and alkali resistant
- Solvent-free

APPLICATION

ALSAN 172 is used for the pre-treatment (primer and barrier) of asphalt substrates (e.g. mastic asphalt) ready for the later application of ALSAN PMMA resins.

PACKAGING

Can of 10 kg.
ALSAN 172 is supplied without ALSAN 070 catalyst.

COLOURS

ALSAN 172 is unpigmented.

STORAGE

Store in original sealed packaging in a cool, dry and frost-free place. Avoid warm storage areas (> 30 °C) even for brief periods, for example on site. Consequently, the products must not be exposed to direct sunlight or kept in a vehicle. Unopened products have a shelf life of at least 12 months. After opening, reseal the packaging so it is completely airtight.

PRODUCT APPLICATION

Temperatures

The product can be applied within the following temperature ranges:

Product	Temperature range in °C		
	Air	Substrate*	Resins
ALSAN 172	-5 to +35	+3 to +50*	+3 to +30

*The substrate temperature must be at least 3 °C above the dew point during application and curing.

Moisture

The relative humidity must be ≤ 90 %.

The surface to be coated must be dry.

The surface must be protected from moisture until the coating has hardened.

Substrates can be coated provided they are properly prepared.

Please refer to the appropriate application guide for information about correct surface preparation.

ALSAN 172

TECHNICAL DATA SHEET APTDS-E-68-01

REACTION TIMES & REQUIRED AMOUNTS OF CATALYST

	ALSAN 172 (at 20 °C, 3% catalyst)
Pot life	approx. 15 min.
Rain proof after	approx. 30 min.
Can be walked on / over coated after	approx. 45 min.
Curing time	approx. 3 h.

Higher temperatures or greater proportions of catalyst will reduce reaction times, while lower temperatures and smaller proportions of catalyst will increase reaction times.

The following table indicates the recommended amount of catalyst required to adjust the curing reaction to the temperature.

Substrate temperature in °C, required amount of catalyst in % (reference values)												
-10	-5	+3	5	10	15	20	25	30	35	40	45	50
-	-	6%	6%	4%	4%	2%	2%	2%	2%	1%	1%	1%

CONSUMPTION

Substrate	Consumption
Smooth:	0.4 kg/m ²
Fine-sandy:	0.5 kg/m ²
Rough:	0.8 kg/m ²

TECHNICAL DATA

Density: 1.06 g/cm³

APPLICATION CONDITIONS

Application equipment / tools

Mixing of the product:

- Suitable mixer (ex. paint mixer)

Applying of the product:

- Sheepskin roller
- Brush (only for areas not accessible with the roller)

Substrate preparation

ALSAN 172 must only be applied to a prepared substrate.

Please refer to the appropriate application guide for information about correct surface preparation.

Mixing

First stir the tub contents thoroughly. Then add the catalyst whilst stirring at a low speed for 2 minutes.

Make sure that all material on the side and base of the pot is mixed in. At temperatures below 10 °C the product should be stirred for 4 minutes as the catalyst will take longer to dissolve.

ALSAN 172

TECHNICAL DATA SHEET APTDS-E-68-01

Application

Use the sheepskin roller to apply an even film-forming coat of primer.

Avoid creating puddles of primer.

Once the coating has cured, apply a second coat to cover any defects (bubbles, areas not fully coated).

Preparation for subsequent layers

For the subsequent application of ALSAN 072 RS:

Once the primer has hardened, apply a second layer and sprinkle with a little quartz sand (0.1 – 0.2 kg/m² at 0.2 – 0.6 mm) while the primer is still wet.

The sand finishing creates the necessary key, i.e. roughness, for application of the mortar.

Never apply the sand finishing to the first coat of primer.

CLEANING

When work is interrupted or completed, clean the tools thoroughly with ALSAN cleaning agent within the pot life of the material (approx. 10 minutes). This can be done with a brush. Do not use the tools again until the cleaning agent has fully evaporated.

Simply immersing the tools in the cleaning agent will not prevent the material from hardening.

SAFETY INFORMATION & RISKS

Please refer to the safety data sheet for the relevant product.

QUALITY

SOPREMA has always attached the highest importance to Quality Control. For this reason, we operate an independently monitored Quality Assurance System in line with **EN ISO 9001:2008** and **EN ISO 14001:2004**.



GENERAL INFORMATION

The above information, in particular the product application information, is based on extensive development and many years of experience. It's provided to the best of our knowledge. However, the wide range of requirements and conditions on site means that it may be necessary for the product to be tested under those conditions to ensure that it is suitable for the intended purpose. For further information and questions, contact **SOPREMA**.

Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology and improvements to our products.