

# ALSAN 074

TECHNICAL DATA SHEET APTDS-E-78-01

## DESCRIPTION

**ALSAN 074** is a PMMA based fast-curing and flexible product used to fill small cracks and joints as well as to smooth out areas of minor unevenness. It is used mainly to prepare the substrate before ALSAN PMMA resins are applied.

## MATERIAL

2-component, PMMA based (polymethyl methacrylate) fast-curing, filled and flexible surfacer.

## PROPERTIES

- Easy to apply
- Can be applied at sub zero temperatures
- Fast-curing
- Hydrolysis and alkali resistant
- Solvent-free

## APPLICATION

**ALSAN 074** is used to fill small cracks and joints in order to prepare the substrate before ALSAN PMMA resins are applied. The product can also be used to smooth out fleece overlaps in the waterproofing layer.

## PACKAGING

Can of 5 or 10 kg.

**ALSAN 074** is supplied without ALSAN 070 catalyst.

## COLOURS

**ALSAN 074** is pebble grey (RAL 7032).

## STORAGE

Store in original sealed packaging in a cool, dry and frost-free place. Avoid warm storage areas (> 30 °C) even for brief periods, for example on site. Consequently the products must not be exposed to direct sunlight or kept in a vehicle. Unopened products have a shelf life of at least 12 months. After opening, reseal the packaging so it is completely airtight.

## PRODUCT APPLICATION

### Temperatures

The product can be applied within the following temperature ranges:

Product	Temperature range in °C		
	Air	Substrate*	Resins
ALSAN 074	-5 to +35	-5 to +50*	+3 to +30

\*The substrate temperature must be at least 3 °C above the dew point during application and curing.

### Moisture

The relative humidity must be ≤ 90 %.

The surface to be coated must be dry.

The surface must be protected from moisture until the coating has hardened.

Substrates, e.g. young concrete, containing residual moisture can be coated provided it has set sufficiently and the substrate is properly prepared.

Please refer to the appropriate application guide for information about correct surface preparation.

# ALSAN 074

TECHNICAL DATA SHEET APTDS-E-78-01

## REACTION TIMES & REQUIRED AMOUNTS OF CATALYST

	ALSAN 074 (at 20 °C, 3% catalyst)
Pot life	approx. 15 min.
Rain proof after	approx. 30 min.
Can be walked on / over coated after	approx. 30 min.
Curing time	approx. 3 h.

Higher temperatures or greater proportions of catalyst will reduce reaction times, while lower temperatures and smaller proportions of catalyst will increase reaction times.

The following table indicates the recommended amount of catalyst required to adjust the curing reaction to the temperature.

Substrate temperature in °C, required amount of catalyst in % (reference values)												
-10	-5	+3	5	10	15	20	25	30	35	40	45	50
-	-	4%	4%	4%	2%	2%	2%	2%	2%	1%	1%	1%

## CONSUMPTION

Substrate	Consumption
Smoothing fleece overlaps	0.30 kg/m run
Filling	1.5 - 2 kg/m <sup>2</sup> /mm

## TECHNICAL DATA

Density: 1.71 g/cm<sup>3</sup>

## APPLICATION CONDITIONS

### Application equipment / tools

Mixing of the product:

- Suitable mixer (ex. paint mixer)

Applying of the product:

- Smoothing trowel or finishing trowel

### Substrate preparation

ALSAN 074 is applied to the hardened ALSAN PMMA Primers. See technical guidelines of the primer.

### Mixing

First stir the tub contents thoroughly. Then add the catalyst whilst stirring at a low speed for 2 minutes. Make sure that all material on the side and base of the pot is mixed in. At temperatures below 10 °C the product should be stirred for 4 minutes as the catalyst will take longer to dissolve.

### Application

Fill in small cracks or joints using a pointing trowel or finishing trowel. Use the pointing trowel to smooth over minor differences in height.

### Preparation for subsequent layers

None required.



# ALSAN 074

TECHNICAL DATA SHEET APTDS-E-78-01

## CLEANING

When work is interrupted or completed, clean the tools thoroughly with ALSAN cleaning agent within the pot life of the material (approx. 10 minutes). This can be done with a brush. Do not use the tools again until the cleaning agent has fully evaporated.

Simply immersing the tools in the cleaning agent will not prevent the material from hardening.

## SAFETY INFORMATION & RISKS

Please refer to the safety data sheet for the relevant product.

## QUALITY

**SOPREMA** has always attached the highest importance to Quality Control. For this reason, we operate an independently monitored Quality Assurance System in line with **EN ISO 9001:2008** and **EN ISO 14001:2004**.



## GENERAL INFORMATION

The above information, in particular the product application information, is based on extensive development and many years of experience. It's provided to the best of our knowledge. However, the wide range of requirements and conditions on site means that it may be necessary for the product to be tested under those conditions to ensure that it is suitable for the intended purpose. For further information and questions, contact **SOPREMA**.

Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology and improvements to our products.