

ASPHALT REPAIR

FOR ASPHALT SURFACES



ASPHALT REPAIR is composed of a ready-to-use mixture of adherent aggregates. It forms a solid bond with all firm surfaces, whether wet or dry.

- Can be installed at any temperature
- Extends the service life of asphalted surfaces

PRODUCT PURPOSE

Application	Asphalt surface protection
Substrate	Asphalt

PRODUCT CHARACTERISTICS

Installation Method	Trowel or shovel applied
---------------------	--------------------------

PACKAGING

Code	Containers	Coverage	Bags per skid
26301	10 kg	3 potholes of 1 ft x 1 ft x 1 in	100
20628	20 kg	5 potholes of 1 ft x 1 ft x 1 in	56

INSTALLATION

Storage	2 years in the original container. Can be stored at temperature below 0 °C (32 °F).
---------	-------------------------------------------------------------------------------------

Minimum Application Temperature	Can be used at asphalt temperatures ranging from -40 °C to 76°C (-40 °F to 168 °F).
---------------------------------	-------------------------------------------------------------------------------------

Surface Preparation	The substrate must be dry and free of dust, grease or other contaminants. Remove crumbled asphalt or any loose material and remove ponding water.
---------------------	---------------------------------------------------------------------------------------------------------------------------------------------------

Installation Prerequisite	The RESISTO ASPHALT REPAIR is designed to fill potholes and cracks of 3/4 in. (20 mm) and more.
---------------------------	-------------------------------------------------------------------------------------------------

Installation	<ol style="list-style-type: none"> 1. Fill the holes with ASPHALT REPAIR until the product overflows. Compact the product with a sledge hammer and a plywood or a vibratory rammer. 2. The product must be pressed laterally to reach a proper level of repaired area. For a better compaction, immediately let vehicles circulate on the repaired area (the product will not stick to the tires and will not move). 3. Seal the container tightly.
--------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Drying time	15 days. Drying time may vary depending on ambient temperature, humidity level and the amount applied. The product must have a cure long enough (firm and dry to the touch), before applying a RESISTO ASPHALT DRIVEWAY SEALER.
-------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Cleaning	Clean damp tools with water. When dry, clean with solvents such as mineral spirits, paint thinner or xylene.
----------	--------------------------------------------------------------------------------------------------------------

Tricks / Tips	To reduce curing time after compaction and to limit stickiness of repaired areas, sprinkle with dry sand. To ensure long-lasting protection of the asphalt surface, seal it using a RESISTO driveway sealer.
---------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Recommendations/ Limitations	Not designed to level ruts (uneven surfaces caused by automobiles weight in parking lots). The product can be used for larger holes when appropriate compaction means are utilized.
------------------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------