## RESISTO

### SUPREME ROOF REPAIR

### MASTIC

A superior plastic cement developed specifically for professional roofers. With a high concentration of bitumen, it seals roof elements such as flashing, vents or upstands and is use to repair various joints, holes and cracks, built-up roofing, etc.

- · Application on all surfaces with optimum bonding
- Excellent resistance to temperature variations
- Use without primer

#### **PRODUCT PURPOSE**

| Application   | Waterproofing |                  |
|---------------|---------------|------------------|
| Building Part | Roofing       | Foundations      |
|               | Walls         | Other            |
| Substrates    | Wood          | Asphalt shingles |
|               | Concrete      | Metal            |

#### **PRODUCT CHARACTERISTICS**

| Installation Method   | Extruder                           | Trowel |
|-----------------------|------------------------------------|--------|
| Operating Temperature | -40 °C to 80 °C (-40 °F to 176 °F) |        |

#### PACKAGING

| Code  | Containers      | Quantity per Pallet |
|-------|-----------------|---------------------|
| 53017 | 300 ml (10 oz)  | 1200                |
| 53019 | 4 kg (2.2 lb)   | 120                 |
| 53023 | 13.6 kg (30 lb) | 48                  |
| 53022 | 20 kg (44 lb)   | 36                  |

#### PROPERTIES

| Properties       | SUPREME ROOF REPAIR        |  |
|------------------|----------------------------|--|
| Color            | Black                      |  |
| Solids by Weight | 83.5%                      |  |
| Flow             | None at these temperatures |  |

All values are nominal)

Meets or exceeds the requirements of CAN/CGSB-37.5M89 standard.



# RESISTO

### SUPREME ROOF REPAIR

#### INSTALLATION

| Storage                            | Two years in its original closed packaging, in a cool, well-ventilated area. Store in a cool, dry place up to 40 ° C (104 ° F). The product can withstand freezing.   |  |
|------------------------------------|---|--|
| Minimum Application<br>Temperature | 0 °C (32 °F). The product must be at a minimum temperature of 10 ° C (50 ° F) before application.   |  |
| Tools Required                     | K Extruder K Trowel   |  |
| Surface Preparation                | The substrate must be clean and free of dust, grease or other contaminants.   |  |
| Installation<br>Drying time        | Apply with a trowel or an extruder.   Between 4 and 24 hours, depending on ambient temperature and the amount applied.  |  |
| Recommendations/<br>Limitations    | Do not apply strips greater than 1 cm (1/2 in) in width. It is not recommended to use a product containing bitumen directly on softwood boards or on flexible polyvinyl chloride.   |  |
| Warnings                           | Keep out of the reach of children. Properly close the container after each use. Keep out of the sun and away from ignition sources. During use, keep away from ignition sources. No smoking. After application, keep away from flames until solvent has evaporated. Do not pour residues in drains. |  |





resisto.ca | resisto.us