

PRODUCT DATA SHEET

DESCRIPTION

FLAGON® S is a synthetic flexible PVC-P membrane used in detailing work and distinguished by a very high resistance to weathering conditions and UV rays.

STORAGE & HANDLING

Rolls must be stored in upright position. Store rolls in a clean dry location and cover as necessary to protect from any environmental impact such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of FLAGON® S.

USER APPLICATION

FLAGON® S can be used in single ply or 2-ply, vertically and horizontally in substructure and superstructure applications. All the application guidelines are described in SOPREMA's Technical Manuals in force.

ADVANTAGES

- High resistance to weathering conditions
- Excellent resistance soil chemicals
- Excellent weldability
- Flexible



HEALTH, SAFETY & ENVIRONMENT

The product does not contain any substance likely to be detrimental to health or to the environment and complies with generally admitted Health & Safety Requirements. For further information please refer to relevant Material Safety Data Sheet (MSDS).

TRACEABILITY

Product traceability is ensured through a manufacturing identification present on the packaging.

QUALITY MANAGEMENT

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality Management Systems in line with ISO 9001:2015.

COMPOSITION & PACKAGING

PROPERTY	FLAGON® S
Thickness	1.5 mm
Roll dimension	1.05 x 20 m
Roll weight	41 kg
Rolls per pallet	46 Rolls

TECHNICAL PROPERTIES

PROPERTY	STANDARDS	FLAGON® S
Tensile strength	EN 12311-2, met B)	15 N / mm ²
Elongation at max load	EN 12311- 2, met B	300 %
Nail tear resistance	EN 12311- 2, met B	80 N
Resistance to impact	EN 12691	800 mm
Foldability at low temperature	EN 495-5)	-30 °C
Watertightness	EN 1928, met B)	conform
Durability: exposure to UV, heat and water	EN 1297	grade 0
Resistance to static loading	EN 12730, met A	20 kg
Reaction to fire	EN 11925-2 / EN 13501-1	E

Note: All products manufactured by SOPREMA comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

Data is represented by average values, unless noted otherwise.

All values are nominal.

TESTING AND CERTIFICATIONS



SUSTAINABILITY AND ENVIRONMENT

