

SOPRA-XPS 60 & 60 PL

TECHNICAL DATA SHEET 211111SCANE

(Supersedes 210812SCANE)



INSULATION

APPLICATIONS

FOUNDATIONS

ROOFS

PARKING DECKS

PLAZA DECKS

DESCRIPTION

SOPRA-XPS 60 are rigid thermal insulation boards made of high-density extruded polystyrene with square edges on their four sides. They are composed of closed cell foam. They are mainly used for **SOPREMA** foundation systems under slabs, civil engineering applications, protected-membrane roofing systems (inverted), parking decks and plaza decks.

SOPRA-XPS 60 PL are rigid thermal insulation boards made of high-density extruded polystyrene specifically designed for **SOPREMA** plaza deck system applications. They are available with channels on the lower long sides to facilitate water drainage.

The optimized formula of **SOPRA-XPS 60 & 60 PL** contains no CFC, no HCFC and no HFC 134a. Moreover, this formula has zero ozone depletion potential and a very low global warming potential of 1.

SOPRA-XPS 60 & 60 PL meet GREENGUARD GOLD certification.

INSTALLATION

LOOSE LAID

The **SOPRA-XPS 60 & 60 PL** insulation boards are laid flat on the roof, parking decks, plaza decks and on the ground for applications under concrete slabs. When installing **SOPRA-XPS 60 PL**, make sure that channels are facing downwards to allow water to drain. When another layer of **SOPRA-XPS 60** insulation is required, it should be installed with staggered joints without being adhered to the first layer. If necessary, use with **SOPRASEAL LM 200 T** adhesive or an adhesive compatible with extruded polystyrene to hold the boards together temporarily.

ADHERED WITH ADHESIVE

Adhere with **SOPRASEAL LM 200 T** adhesive or an adhesive compatible with extruded polystyrene.

Maximum service temperature: 75 °C (167 °F).

Note: **SOPRA-XPS 60 & 60 PL** should not be exposed to uv rays for more than 60 days.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

PACKAGING

Specifications	SOPRA-XPS 60	SOPRA-XPS 60 PL ⁽²⁾
Colour	Grey	
Board dimensions ⁽¹⁾	2438 mm x 610 mm (8 x 2 ft)	
Available thicknesses ⁽¹⁾	25 mm (1 in) 38 mm (1.5 in) 51 mm (2 in) 63 mm (2.5 in) 76 mm (3 in) 87 mm (3.5 in)	51 mm (2 in) 76 mm (3 in)
		Channel dimensions 

(All values are nominal)

(1) Other thicknesses and dimensions available upon request.

(2) Product available upon special order only.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS_SOPRA-XPS_60_&_60_PL.indd

SOPRA-XPS 60 & 60 PL

TECHNICAL DATA SHEET 211111SCANE

(Supersedes 210812SCANE)



INSULATION

APPLICATIONS

FOUNDATIONS

ROOFS

PARKING DECKS

PLAZA DECKS

PROPERTIES

SOPRA-XPS 60 & 60 PL meet the requirements of ASTM C578-14 Type VII.

SOPRA-XPS 60 & 60 PL meet the requirements of CAN/ULC S701.1 Type 4.

Properties	Standards	SOPRA-XPS 60 & 60 PL
Thermal Resistance ⁽¹⁾ (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])	ASTM C518	RSI- 0.88 (R – 5,0)
Water Vapour Permeance	ASTM E96 (Method A)	52 ng/Pa•s•m ² (0.9 perm)
Flame spread rating	CAN/ULC-S102.2 ⁽²⁾	> 25 < 500
Dimensional Stability, max.	ASTM D2126	1.5 %
Min. Flexural Strength	ASTM C203	1000 kPa (145 psi)
Water Absorption, % by volume, max.	ASTM D2842	0.6
Water Absorption, % by volume, max.	ASTM C272	0.1
Min. Compressive Strength ⁽³⁾	ASTM D1621	415 kPa (60 psi)
Limiting Oxygen Index	ASTM D2863	24 %
Compressive modulus	ASTM D1621	17.5 MPa
Global recycled content ⁽⁴⁾	-	75 %

For CCMC product evaluation see CCMC Evaluation listing 14149-L

(All values are nominal)

- (1) The long-term thermal performance (LTTR) of SOPRA-XPS 60 & 60 PL complies with CAN/ULC S701.1 standard requirement: min. RSI-1.66 (R-9.4) for Type 4 products that are 50 mm (2 in) thick. Please consult your SOPREMA representative for more information.
- (2) CAN/ULC S102.2 : Standard Method of Test for Surface Burning Characteristics of Flooring, Floor Covering, and Miscellaneous Materials and Assemblies.
- (3) At 5 % deformation or yield.
- (4) The recycled content varies according to the compression range. The global recycled content is made of one part post- and pre-consumer content validated by CT Consultant, and another part which accounts for the manufacturing process recovery value. The specific details of the products covered by this validation can be found on the Recycled Content Certificate available on our website.

STORAGE AND HANDLING

SOPRA-XPS 60 & 60 PL thermal insulation boards are covered with a temporary waterproof packaging for handling the panels in the manufacturing plant and during transit.

SOPRA-XPS 60 & 60 PL thermal insulation boards must be stored on a flat substrate in their original packaging. If the products are stored outdoors, cover them with an opaque protective cover if the original packaging is removed so that the boards are always protected from UV and sheltered from inclement weather. As they are flammable, they must be protected and kept away from flames and intense heat sources during transportation, handling, storage, and installation.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS_SOPRA-XPS_60_&_60_PL.indd