

ASPHALT DRIVEWAY SEALER 2 AND 4 YEARS - ASPHALT EMULSION PROTECTION



An asphalt water-based emulsion coating used to prevent cracks and deterioration of asphalt pavements caused by wear and tear, freezing, oil and gasoline spills, salt, sun and rain.

- Restores some of the original properties and elasticity of asphalt surfaces
- No unpleasant smell
- Easy and fast application

PRODUCT PURPOSE

Application	Asphalt surface protection
Substrate	Asphalt

PRODUCT CHARACTERISTICS

Installation Method	Squeegee
---------------------	----------

PACKAGING

Code	Containers	Indicative Covering	Quantity per Pallet
50318 (2 years)	17 l (4.5 US gal)	18.6 to 37.2 m ² (200 to 400 ft ²)	36
50320 (4 years)	17 l (4.5 US gal)		36

INSTALLATION

Storage	12 months in the original container. Store in a cool, dry place, between 10 ° C (50 ° F) and 40 ° C (104 ° F). Keep away from frost.
Minimum Application Temperature	10 ° C (50 ° F). Do not apply when temperatures below 50°F (10 °C) are expected within 24 hours of application.
Surface Preparation	The substrate must be clean and free of dust, grease or other contaminants.
Installation Prerequisite	Before hand repair the surface with RESISTO asphalt maintenance range of products.
Installation	<ol style="list-style-type: none"> 1. Mix thoroughly until smooth. To facilitate the mixing of the coating, we recommend using a drill equipped with a mixer attachment. 2. Starting at the highest part of the area to be covered, pour DRIVEWAY SEALER in ribbon shapes over the asphalt. 3. Apply the sealer with a squeegee, taking care not to leave any excess product on the surface. 4. Let the surface dry and then check for the hardening of the product before allowing normal traffic. Product's color will turns from brown to black when dry.
Drying time	24 to 48 hours. 48 hours before parking a vehicle.
Cleaning	Clean damp tools with water. When dry, clean with solvents such as mineral spirits, paint thinner or xylene.
Tricks / Tips	For best results, do not apply the product in direct sunlight.
Recommendations/ Limitations	Avoid applying the product if there is a risk of rain, high humidity or frost within 24 hours of application. Do not apply on a surface if a coal-tar-pitch-based sealer has been applied and is still in good condition. The asphalt repair surface must cure for a minimum of 15 days before the application of the ASPHALT PROTECTOR.