

# SOPRA-ISO PLUS SHIPLAP BOARD

TECHNICAL DATA SHEET 210803SCANE

(supersedes210512SCANE)



INSULATION

APPLICATIONS

ROOFS

## DESCRIPTION

SOPRA-ISO PLUS SHIPLAP BOARD is a polyisocyanurate thermal insulation board with shiplap edges on four (4) sides. It is composed of a closed cell polyisocyanurate foam core between polymers coated glass fibres facers.

It is mainly use as thermal insulation for SOPREMA roofing systems.

SOPRA-ISO PLUS SHIPLAP BOARD meets GREENGUARD GOLD certification.

## INSTALLATION

### MECHANICALLY FASTENED

Mechanically fastened with screws and stress plates for insulation.\*

### ADHERED WITH HOT BITUMEN

Adhered with hot bitumen (the temperature of the bitumen must be 10 °C [50 °F] below the Equiviscous Temperature [EVT<sup>1</sup>]).

### ADHERED WITH ADHESIVE

Adhered with one of the DUOTACK adhesives.\*

**Service temperature:** -73 to 122 °C (-100 to 250 °F).

\* The required number of mechanical fasteners and amount of adhesive varies from zone to zone. For more details about these requirements, consult the Wind Uplift Resistance Testing reports according to Canadian standard CSA A123.21 or Factory Mutual (FM 4470).

(1) Equiviscous Temperature (EVT): The temperature at which bitumen reaches an ideal viscosity threshold of 125 cP (0.125 Pa·s), which guarantees the quantity of mop-applied inter-ply asphalt used in laminated roofing systems (www.roofingcanada.com).

## RESTRICTIONS

Waterproofing membranes must not be adhered directly to SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation board, except COLVENT BASE 830 (without primer) and COLVENT BASE 840 (with primer). Otherwise, a recovery board for roofing must be put in place before the installation of any other waterproofing membranes. SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation boards of 1200 x 2400 mm (4 ft x 8 ft) must not be adhered with hot bitumen or adhesive (see chart below).

Installation methods	Board 1.2 x 1.2 m (47.4 x 47.4 in)	Board 1.2 x 2.4 m (47.4 x 96 in)
Mechanically fastened	Wook deck ONLY	YES
Adhered with hot bitumen	YES	NO
Adhered with adhesive	YES	NO

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

# SOPRA-ISO PLUS SHIPLAP BOARD



INSULATION


APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 210803SCANE

(supersedes 210512SCANE)

## PACKAGING

Specifications	SOPRA-ISO PLUS SHIPLAP BOARD
Thickness	88.9 to 152.4 mm (3.5 to 6 in)*
Dimensions of the boards	1.2 x 1.2 m (47.4 x 47.4 in) 1.2 x 2.4 m (47.4 x 96 in)
Shiplap dimensions	
Surface	Inlymers coated glass fibres facers
Underface	Inlymers coated glass fibres facers

(All values are nominal)

\* Others thicknesses available uinn request.

## PROPERTIES

SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation meets the physical property requirements of ASTM C 1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC S704 Type II (20 psi) and Type III (25 psi).

Properties	Standards	SOPRA-ISO PLUS SHIPLAP BOARD
Thermal Resistance (LTTR) (RSI-Value [R Value] / 25.4 mm [1 in] @ 24 °C [75 °F])	CAN/ULC S770	3.60 RSI (R – 20.5) 4.15 RSI (R – 23.6) 4.72 RSI (R – 26.8) 5.25 RSI (R – 29.8) 6.29 RSI (R – 35.7)
Metal Deck Maximum Flute Spanability (based on SOPRA-ISO thickness)	-	66.70 mm (2 5/8 in)  111.10 mm (4 3/8 in)
Compressive Strength	ASTM D1621	138 kPa (20 psi) 172 kPa (25 psi)
Density	ASTM D1622	32 kg/m <sup>3</sup> (2.0 lb/ft <sup>3</sup> )
Linear Dimensional Stability	ASTM D2126	< 0.5 %
Water Absorption	ASTM C209 ASTM D2842	< 1.0 % < 3.5 %
Flame Spread*	ASTM E84	40 - 60
Tensile Strength	ASTM D1623	35 kPa (> 730 lb/ft <sup>2</sup> )

(All values are nominal)

\* The numerical ratings as determined by ASTM Test Method E84 are not intended to reflect hazards presented by this or any other material under actual fire conditions.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

TDS\_SOPRA-ISO\_PLUS\_SHIPLAP\_BOARD.incd

# SOPRA-ISO PLUS SHIPLAP BOARD

TECHNICAL DATA SHEET 210803SCANE

(supersedes210512SCANE)



INSULATION

APPLICATIONS

ROOFS

## STORAGE AND HANDLING

The SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation boards are covered with a waterproof packaging for handling the panels in the manufacturing plant and during transit only.

SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation boards must be stored on a flat substrate and sheltered from inclement weather. In addition, the temporary SOPREMA applied packaging must be removed to prevent accumulation of condensation.

When short-term outdoor storage is necessary, SOPRA-ISO PLUS SHIPLAP BOARD thermal insulation boards must be stacked on skids at least 75 mm (3 in) above the ground, store flat and cover with a waterproof cover such as a canvas tarpaulin.

Refer to PIMA Technical Bulletin n° 109: Storage & Handling Recommendations for Polyiso Roof Insulation at [www.polyiso.org](http://www.polyiso.org).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.