# **ALSAN FOAM** UNI W 500 ml

# CESSORY

SOPREMA

UNI W

()

### INSULATING FOAM POLYURETHANE (PU)

Format	500 ml (20 oz)	
Colour	Light yellow	
Paintable	No	
Skinning time	6 minutes	
Curing time	24 hours	
Application temperatures	-20 to 30 °C (4 to 86 °F)	
Service temperatures	-40 to 80 °C (-40 to 176 °F)	
Adhesion to wet surfaces	Yes	
Performances	Specific gravity: 1.2 lb/ft <sup>3</sup>	
Performances	Class 1 - CAN/ULC-S701.1	
Shelf life (months)	15	
Product code	24722	
Quantity per box	12	
Quantity per pallet	1,920	

#### FEATURES AND BENEFITS

- Won't bow door and window frames
- Insulating and sealing

DEAL FOR

DOORS AND WINDOWS

- Application in a wide range of temperatures: -20 to 30 °C (4 to 86 °F)
- High-performance formula; requires fewer cartridge changes
- Chemical base: Polyurethane (PU)

# **RECOMMENDED USES**

- Outdoor and indoor use
- Formulated to air seal gaps around rough opening of windows and doors
- Blocks drafts and saves energy
- Permanent adhesion to vinyl, wood, and metal, in addition to being airtight and waterproof
- Wiring and plumbing penetrations and HVAC ductwork.
- Waterproofing of foundation sills, edge joists, attic access hatches, and pest entry points

# COMPLEMENTARY TO OTHER RESISTO PRODUCTS





REDZONE CORNER GUARD

AIR AND VAPOR

**REDZONE 25** 

BARRIER MEMBRANE





ALL-WEATHER BUTYL FLASHING TAPE

#### SURFACE PREPARATION

Before application, be sure that surfaces are clean, homogeneous and free from all contamination (oils and grease, dust, and loose or friable particles). Cement laitance must be removed. Dry and porous surfaces must be moistened with water. The container application temperature is between 5 and 25 °C (41 and 77 °F). Optimal container temperature is approximately 20 °C (68 °F). If the container temperature is lower, place it in lukewarm water (35 to 40 °C [95 to 104 °F]) for 40 minutes.

#### **APPLICATION**

#### Application temperatures: -20 to 30 $^\circ\text{C}$ (-4 to 86 $^\circ\text{F}).$

Service temperatures: -40 to 80 °C (-40 to 176 °F).

Shake the can containing ALSAN FOAM UNI W before use. Screw the can onto an application gun. Press the trigger of the gun to let the foam flow. Shake regularly during the application. Always keep the can upside down during application. During short work interruptions (less than 48 hours), the can may be left screwed onto the gun, but the screw on the back side of the gun must be tightened. The can must be under pressure, otherwise the foam will harden in the gun. Read the gun manufacturer's instructions for proper use of the application tool.

#### RESTRICTIONS

ALSAN FOAM UNI W is not suitable for PE, silicone and PTFE substrates.

#### PROPERTIES

PROPERTIES	ALSAN FOAM UNI W (500 ml)		
Density (foam)	21 kg/m <sup>3</sup>		
Curing system	Moisture		
Skinning time	6 min (+23 °C [73 °F] / 50 % R.H.)		
Curing time	24 hours (+23 °C [73 °F] / 50 % R.H.)		
Fire class	Class 1 - CAN/ULC-S710.1		
Thermal condictivity	0.036 W/m.K (@20 °C [68 °F])		
Compression strength	0.03 MPa		

(All values are nominal)

#### CLEANING

For longer work interruptions, clean the gun with ALSAN FOAM CL-F cleaner.

#### **STORAGE AND HANDLING**

This product may be kept for a period of 15 months from the date of production if stored in its undamaged, unopened original packaging. Store in dry conditions protected from direct sunlight at temperatures between 5 and 25 °C (41 and 77 °F).

For more information about the ALSAN product line, please contact your RESISTO representative.





SOPREMA		RESISTO	
SOPREMA.US	SOPREMA.CA	RESISTO.US	RESISTO.CA
1.800.356.3521	1.877.MAMMOUTH	1.800.356.3521	1.877.478.8408