

ASPHALT REPAIR

FOR ASPHALT SURFACES



ASPHALT REPAIR is composed of a ready-to-use mixture of adherent aggregates. It forms a solid bond with all firm surfaces, whether wet or dry.

- Can be installed at any temperature
- Extends the service life of asphalted surfaces

PRODUCT PURPOSE

Application	Asphalt surface protection
Substrate	Asphalt

PRODUCT CHARACTERISTICS

Installation Method	Trowel or shovel applied
---------------------	--------------------------

PACKAGING

Code	Containers	Coverage	Bags per skid
26301	10 kg	2 potholes of 1 ft x 1 ft x 1 in	100
20628	20 kg	4 potholes of 1 ft x 1 ft x 1 in	56

INSTALLATION

Storage	2 years in the original container. Can be stored at temperature below 0 °C (32 °F).
Minimum Application Temperature	Can be used at asphalt temperatures ranging from -40 °C to 76°C (-40 °F to 168 °F). Condition the product at 15 °C (59 °F) prior to use.
Surface Preparation	The substrate must be dry and free of dust, grease or other contaminants. Remove crumbled asphalt or any loose material and remove ponding water.
Installation Prerequisite	The RESISTO ASPHALT REPAIR is designed to fill potholes and cracks of 3/4 in. (20 mm) and more.
Installation	<ol style="list-style-type: none"> 1. Fill the holes with ASPHALT REPAIR until the product overflows. Compact the product with a sledge hammer and a plywood or a vibratory rammer. 2. The product must be pressed laterally to reach a proper level of repaired area. For a better compaction, immediately let vehicles circulate on the repaired area (the product will not stick to the tires and will not move). 3. Seal the container tightly.
Drying time	15 days. Drying time may vary depending on ambient temperature, humidity level and the amount applied. The product must have a cure long enough (firm and dry to the touch), before applying a RESISTO ASPHALT DRIVEWAY SEALER.
Cleaning	Clean damp tools with water. When dry, clean with solvents such as mineral spirits, paint thinner or xylene.
Tricks / Tips	To reduce curing time after compaction and to limit stickiness of repaired areas, sprinkle with dry sand. To ensure long-lasting protection of the asphalt surface, seal it using a RESISTO driveway sealer.
Recommendations/ Limitations	Not designed to level ruts (uneven surfaces caused by automobiles weight in parking lots). The product can be used for larger holes when appropriate compaction means are utilized.