



WATERPROOFING

APPLICATIONS

ROOFS

GREEN ROOFS

PLANTER BOXES

# SOPRALENE FLAM JARDIN CAP

TECHNICAL DATA SHEET

ANZ-TDS-41-SOPRALENE FLAM JARDIN CAP

## DESCRIPTION

SOPRALENE FLAM JARDIN CAP is a flexible SBS elastomeric bitumen waterproofing membrane with a non-woven polyester reinforcement.

The topside of SOPRALENE FLAM JARDIN CAP is protected by slate chippings and the underside is covered by a thermofusible film.

SOPRALENE FLAM JARDIN CAP bitumen mass contains anti-root penetration properties for green roofs and complies with EN 13948 (FLL procedure).

## FIELD OF APPLICATION

Designed to fit for single-ply or two-ply waterproofing assemblies, SOPRALENE FLAM JARDIN CAP membranes are used in vertically and horizontally waterproofing for the following general applications:

- Green roofing
- Plaza decks
- Planter boxes
- Retaining Walls

## APPLICATION METHOD

SOPRALENE FLAM JARDIN CAP is fully heat welded using a propane torch or MINI MACADEN machine.

## INSTALLATION PROCEDURE

### SUBSTRATE

- No work should be started until all surfaces are smooth, dry, and free of ice, snow or any other substance that may prevent the membrane from adhering properly
- Substrate must have a minimum 1% gradient to ensure that water drains to drainage outlets
- Do not install heat welded membranes directly onto combustible substrate
- Concrete substrate must be fully cured before application of the membrane
- Concrete substrate must have a Concrete Surface Profile (CSP) between 3 and 6 as per International Concrete Repair Institute
- Adhesion test is recommended prior to installation
- Commencement of installation shall be taken as acceptance of the substrate by the Applicator

### PRIMING

- When installed as top layer over base sheet membrane, primer is not required
- When installed over concrete or metal surface prime with ANTIROCK PRIMER at the rate specified in the TDS

### HEAT WELDING

- Unroll membrane sheets onto the roof surface
- Starting at the low point of the roof, lay out the membrane to ensure the plies are installed perpendicular to the roof slope, shingled to prevent back-water laps
- Ensure specified side-laps and end-laps are maintained. End-laps should be staggered 1 m apart.
- As the membrane ply is unrolled, apply heat to the underside of the ply until the thermofusible plastic film melts sufficiently for full adhesion to the substrate, and full adhesion between plies
- For hand-held roof torches, continuously move the torch side-to-side across the underside of the roll to melt the bitumen while continuously unrolling sheet. While unrolling and heating the sheet, ensure approximately 6 to 12 mm of hot bitumen flows ahead of the roll, and there is 3 to 6 mm bleed out at all laps. Ensure all side-laps are fully adhered and sealed watertight.

Compliance with AS 4654.1

Anti-root properties

High mechanical properties

High resistance to tear and puncture

High resistance to hydraulic pressure



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS\_SOPRALENE\_FLAM\_JARDIN\_CAP

1/3



WATERPROOFING

APPLICATIONS

ROOFS

GREEN ROOFS

PLANTER BOXES

# SOPRALENE FLAM JARDIN CAP

TECHNICAL DATA SHEET

ANZ-TDS-41-SOPRALENE FLAM JARDIN CAP

## HEAT WELDING (CONT.)

- Adjust application methods to accommodate varying environmental conditions as necessary to achieve the desired results.
- At the 150 mm end-laps ensure a fully adhered watertight seal. Melt the thermofusible plastic film or embed granules and remove other membrane surfacing, where present, using a torch or hot-air welder.
- All penetrations and upturn details should be waterproof as per SOPREMA Installation Guides and detail drawings.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## PACKAGING

SPECIFICATIONS	SOPRALENE FLAM JARDIN CAP
Thickness	4 mm
Roll dimensions	8 m × 1 m
Roll weight	39 kg
Rolls per pallet	30

## PROPERTIES

PROPERTIES	TEST METHOD	SOPRALENE FLAM JARDIN CAP
Abrasion resistance	AS 1580.403.2	PASS
Bond strength to concrete	ASTM C794	1500 N/m
Cyclic movement	CSIRO Moving joint test (B)	PASS
Dimensional stability	ASTM D5147	MD: -0.09 % ; CD: -0.18%
Elongation at break	AS 4654.1	MD: 55 % ; CD: 59 %
Field seam strength	ASTM D1876	36.5 ±8 N/2.5cm
Heat ageing	AS 4654.1 (AS 1145.3)	PASS ; no visual change
Ultraviolet resistance	AS 4654.1 (AS 1145.3)	PASS ; no visual change
Heat resistance	ASTM D4799	110
Tensile strength	ASTM D5147	910 N/5cm ; 530 N/5cm
Durability	AS 4654.1	PASS
Water vapour transmission rate	AS 4654.1	0 perm**
Root resistance	EN 13948	PASS

\*\* The results values are below the variation of the equipment. We consider that the sample have no water vapor transmission



SOPREMA.COM.AU • +61 (3) 9221 6230

2/3



WATERPROOFING

APPLICATIONS

ROOFS

GREEN ROOFS

PLANTER BOXES

# SOPRALENE FLAM JARDIN CAP

TECHNICAL DATA SHEET

ANZ-TDS-41-SOPRALENE FLAM JARDIN CAP

## STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, their representative and/or the contractor is responsible for checking the suitability of products for their intended use.



SOPREMA.COM.AU • +61 (3) 9221 6230

TDS\_SOPRALENE\_FLAM\_JARDIN\_CAP

3/3