

## M2M HIGH-PERFORMANCE REFLECTIVE INSULATION

### INSULATION | VAPOR BARRIER

A 8 mm reflective insulating vapor barrier consisting of two layers of air bubbles, laminated between two metallized polyethylene sheets.

- Installs quickly, easily and provides an excellent R-value
- Reduces condensation, air infiltration, and energy costs

#### PRODUCT PURPOSE

Application	Insulation	
Building Part	Roofs	Walls
	Floors	Ceilings
	Other	

#### PRODUCT CHARACTERISTICS

Surface	Metallized polyethylene	
Underface	Metallized polyethylene	
Installation Method	Stapled	Adhesive tape
Operating temperature	-45 °C to 82 °C (-50 °F to 180 °F)	

#### PACKAGING

Code	Width		Length		Gross area	
	m	ft	m	ft	m <sup>2</sup>	ft <sup>2</sup>
55035	2.44	8	38.10	125.00	92.96	1000
55029	1.22	4	38.10	125.00	46.48	500
55049	1.22	4	19.05	62.50	23.23	250
55000	1.22	4	7.62	25.00	9.29	100
55018	1.22	4	3.81	12.50	4.65	50
55108	0.61	2	19.05	62.50	11.6	125
55002	0.61	2	7.62	25.00	4.65	50
55015 (with staple tab)	0.61	2	7.62	25.00	4.65	50
55005	0.41	1.5	7.62	25.00	3.07	33
55110 (with staple tab on both sides)	0.41	1.5	7.62	25.00	3.07	33
55017 (with staple tab)	0.41	1.5	7.62	25.00	3.07	33
55007 (pipe and round duct wrap)	0.30	1	7.62	25.00	2.33	25
55013 (pipe and round duct wrap)	0.15	6 in	7.62	25.00	1.16	12.5
55014 (pipe and round duct wrap)	0.05	2 in	7.62	25.00	0.39	4.17

\* Other dimensions available on [www.resisto.ca](http://www.resisto.ca)




## M2M

### PROPERTIES

Properties	STANDARDS	M2M
Nominal thickness	-	8 mm (5/16 in)
Emissivity	-	0.03-0.04
Reflectivity	-	0.96-0.97
Compressive strength	-	414kN/m <sup>2</sup> (60.05 lb/in <sup>2</sup> )
Tensile Strength	CAN/CGSB-51.33-M89	3.7 N/mm (21.13 lb/in)
Water vapour permeance	ASTM E96	Conforms type 1
Linear Shrinkage	-	None
Flame spread	ASTM E84	10
Smoke development	ASTM E84	30
Resistance to fungi and bacteria	-	Does not promote growth
Electric conductivity	-	None
Corrosivity, 200 °F (93 °C) - 7 days	-	Pass
Pliability	CAN / CGSB-51.33 M89	No cracking

(Nominal values)  
RESISTO REFLECTIVE INSULATION PRODUCTS ARE TESTED ACCORDING TO ASTM C1224, ASTM C1363 AND ASTM C518 STANDARDS

### INSTALLATION

Storage	Store rolls upright, in a dry and heated place to limit the risk of condensation.	
Complementary Products	ADHESIVE TAPE ALUMINUM	ADHESIVE TAPE METALLIZED
	ADHESIVE TAPE WHITE VINYL	
Tools Required	 Knife	 Tape measure
	 Stapler	

Surface Preparation	All cracks and surface holes should be repaired before installing an HIGH-PERFORMANCE REFLECTIVE INSULATION product. If there is an existing vapor barrier, it must be removed or torn to avoid condensation problems.
Installation	<p>M2M can be stapled, nailed, screwed, glued and threaded. The installation method of these products may have an impact on their efficiency; it is therefore important to know the best installation methods recommended by RESISTO. Furthermore, since RESISTO reflective insulation is also a 100% vapour barrier, it must be installed on the warm side of the assembly, according to the construction standards in your area.</p> <p>Moreover, the use of SPACER STRIPS or wood furring strips is highly advised. They create an air space between the REFLECTING INSULATION and the surface to be insulated to easily obtain maximum insulating value at a low price. The recommended air space should be between 0.5 in to 2 in (1.25 cm to 5 cm).</p>
Tricks / Tips	To minimize air infiltration and humidity transfer, ensure that the HIGH-PERFORMANCE REFLECTIVE INSULATION is not punctured and the insulation system is waterproof. All holes and junctions between two insulation materials must be sealed with RESISTO ADHESIVE TAPE or with a suitable sealant.