

SOPRA-ISO V PLUS

TECHNICAL DATA SHEET 260120SCANE

(supersedes 250701SCANE)



INSULATION

APPLICATIONS

WALLS

DESCRIPTION

SOPRA-ISO V PLUS is a closed-cell polyisocyanurate foam insulation board laminated with a non-reflective glass-mat facer on both sides. SOPRA-ISO V PLUS is used as thermal insulation in SOPREMA's wall systems.

RECOMMENDED SUBSTRATES

This product can be used on most substrates using fasteners or adhesive, such as concrete, wood, wood stud, steel stud, glass-mat gypsum, air/vapour barrier membranes.

INSTALLATION

MECHANICALLY FASTENED

Mechanically fastened with screws and stress plates for insulation.

Minimum penetration depth depending on the substrate:

- Fasteners for wood studs 19.0 mm (3/4 in)
- Fasteners for steel studs 6.5 mm (1/4 in)
- Fasteners for concrete wall 19.0 to 32.0 mm (3/4 to 1 1/4 in)

Service temperature: -60 to 93 °C (-76 to 199 °F)

RESTRICTIONS

SOPRA-ISO V PLUS is not a structural product. SOPRA-ISO V PLUS must not be left exposed for more than 60 days.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	SOPRA-ISO V PLUS
Thicknesses ⁽¹⁾	13.0 to 102.0 mm (0.5 to 4.0 in)
Dimensions ⁽¹⁾	1.2 x 2.4 m (4 x 8 ft)
Surface	Non-reflective glass-mat facer
Underface	Non-reflective glass-mat facer

(1): Other thicknesses and dimensions available upon request.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

1/3

SOPRA-ISO V PLUS



INSULATION

APPLICATIONS

WALLS

TECHNICAL DATA SHEET 260120SCANE

(supersedes 250701SCANE)

PROPERTIES

SOPRA-ISO V PLUS meets or exceeds the following properties.

Properties		Standards	SOPRA-ISO V PLUS
Thermal values (LTTR) ⁽¹⁾ , as per available board thicknesses	12.7 mm (0.5 in) 19.1 mm (0.75 in) 25.4 mm (1.0 in) 38.1 mm (1.5 in) 50.8 mm (2.0 in) 63.5 mm (2.5 in) 76.2 mm (3.0 in) 88.9 mm (3.5 in) 101.6 mm (4.0 in)	CAN/ULC S770 and CAN/ULC S704.1: 2017 Type 2, Class 2	0.49 RSI (R - 2.80) 0.74 RSI (R - 4.22) 0.99 RSI (R - 5.63) 1.50 RSI (R - 8.49) 2.01 RSI (R - 11.40) 2.52 RSI (R - 14.34) 3.05 RSI (R - 17.31) 3.58 RSI (R - 20.32) 4.11 RSI (R - 23.36)
Long term thermal resistance (LTTR),	25 mm (1.0 in) 50 mm (2.0 in) 75 mm (3.0 in)	CAN/ULC S770 and CAN/ULC S704.1: 2017 Type 2, Class 2	0.98 RSI (R - 5.63) 1.97 RSI (R - 11.40) 3.00 RSI (R - 17.31)
Tensile strength		ASTM D1623	> 35 kPa (5.08 psi)
Flexural strength		ASTM C203	> 275 kPa (40 psi)
Compressive Strength		ASTM D1621	> 140 kPa (20 psi)
Water vapour permeance, at 25.4 mm (1 in)		ASTM E96 (Procedure A)	58 ng/Pa•s•m ² (1.01 perm)
Water absorption		ASTM D2842	1.1% by volume
Dimensional stability, at -29 °C (-20 °F), ambient humidity at 80 °C (176 °F), ambient humidity at 70 °C (158 °F), 97 % relative humidity		ASTM D2126	< 0.5%
Flame spread		CAN/ULC S102	> 25 < 500
Flame spread		ASTM E84	< 75
Smoke development		ASTM E84	< 450

(All values are nominal)

For CCMC product evaluation see CCMC Evaluation listing CCMC 14288-L.

(1): Conditioned thermal values were determined by ASTM Test Method C518 at 23.9 °C (75 °F) mean temperature. Test specimens were conditioned in accordance with procedures outlined in the CAN/ULC S770 and the CAN/ULC S704.1: 2017 standards.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

SOPRA-ISO V PLUS

TECHNICAL DATA SHEET 260120SCANE

(supersedes 250701SCANE)



INSULATION

APPLICATIONS

WALLS

STORAGE AND HANDLING

SOPRA-ISO V PLUS boards are fully covered with a waterproof packaging designed to protect the product. If the packaging was damaged during transport, it is recommended to remove it in order to eliminate any moisture that may have infiltrated beneath it.

For short-term outdoor storage:

- Stack the boards flat on skids, at least 75 mm (3 in) above the ground.
- Cover the boards with a waterproof covering, secured to prevent displacement by the wind.

Refer to PIMA Technical Bulletin No. 109: *Storage & Handling Recommendations for Polyiso Roof Insulation* at www.polyiso.org.

TESTS, CERTIFICATIONS AND EVALUATIONS



FOR MORE INFORMATION, REFER TO THE INSTRUCTIONS ON THE LABEL AND RELEVANT SAFETY DATA SHEET (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH