

ELASTOCOL STICK ZERO



TECHNICAL DATA SHEET **251113SCANE**

(supersedes 250527SCANE)

DESCRIPTION

ELASTOCOL STICK ZERO is a primer composed of synthetic polymers, adhesive enhancing resins and solvents. It is designed to enhance the adhesion of self-adhesive membranes on various substrates including porous surfaces such as exterior gypsum boards at temperatures above -10 °C (14 °F).

SURFACE PREPARATION

Surfaces must be dry, clean, and free of any oil, grease, debris, or dirt.

APPLICATION

APPLICATION STEPS

1. Mix the container of ELASTOCOL STICK ZERO primer prior to installation.
2. Apply the ELASTOCOL STICK ZERO primer using a brush or a roller.
3. Before installing the waterproofing membrane make sure the primer is dry to touch and that the film doesn't stick to your skin.

Application temperature above: -10 °C (14 °F)

WARNING: Do not accelerate drying of ELASTOCOL STICK by heating it with a torch.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

| Specifications | ELASTOCOL STICK ZERO |
|----------------|---------------------------------|
| Packaging | 19 L (5 US gal) |
| Colour | Red |
| Drying time | 30 to 90 minutes ⁽¹⁾ |

(1): Drying times are approximate and may vary depending on temperature and the amount applied.

COVERAGE

| Substrate type | Coverage per 19 L (5 US gal) container ⁽¹⁾ |
|----------------|--|
| Porous | 47 to 95 m ² (517 to 1 034 ft ²) |
| Non-porous | 76 to 190 m ² (827 to 2 069 ft ²) |

(1): Coverage rate is approximate and may vary due to the application technique and surface roughness.



ELASTOCOL STICK ZERO



TECHNICAL DATA SHEET 251113SCANE

(supersedes 250527SCANE)

PROPERTIES

| Specifications | Standards | ELASTOCOL STICK ZERO |
|--|---------------|----------------------------|
| Specific Gravity, at 25 °C (77 °F) | - | 0.97 kg/L (8.10 lb/US gal) |
| Solids by Weight | - | 49% |
| VOC content | EPA SCAQMD | ~ 0 g/L ~ 240 g/L |
| Viscosity, at 25 °C (77 °F), (Brookfield) | - | 200 - 400 cP |

(All values are nominal)

CLEANING

The uncured adhesive on tools can be cleaned with solvents such as mineral spirits, Varsol, xylene, etc.

STORAGE AND HANDLING

- ELASTOCOL STICK ZERO can be kept 60 months when properly stored in its original sealed containers.
- Store in a cool and well ventilated area. Keep away from any source of heat, dampness, humidity or oxidizing agents.
- ELASTOCOL STICK ZERO is a flammable product. Keep it protected from sunlight and away from any flame. During use, no sources of ignition should be present. Do not smoke. After application, do not approach any flame until solvents have been eliminated.
- In closed area, ensure proper ventilation, using forced ventilation if necessary, and arrange for monitoring from outside.
- Harmful if inhaled, swallowed or when in contact with the skin. Do not pour residues in drains.

TESTS, CERTIFICATIONS AND EVALUATIONS



FOR MORE INFORMATION, REFER TO THE INSTRUCTIONS ON THE LABEL AND RELEVANT SAFETY DATA SHEET (SDS).



SOPREMA.CA 1 877 MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.
This technical data sheet applies to products sold on the Canadian market only.